

## Trap filling experiments on the N2 DLTS signal of CIGS solar cells

Lisanne Van Puyvelde,<sup>a</sup> Johan Lauwaert,<sup>a</sup> Marc Burgelman,<sup>b</sup> Ayodhya N. Tiwari,<sup>c</sup> Henk Vrielinck<sup>a</sup>

<sup>a</sup> Ghent University, Department of Solid State Sciences, Research Group Defects in Semiconductors, Krijgslaan 281-S1, B-9000 Gent, Belgium

<sup>b</sup> Ghent University, Department of Electronics and Information Systems, Research Group Solar Cells, Sint-Pietersnieuwstraat 41, B-9000 Gent, Belgium

<sup>c</sup> Laboratory for Thin-Films and Photovoltaics, EMPA, Swiss Federal Laboratories for Materials Science and Technology, Ueberlandstrasse 129, CH-8600 Dübendorf, Switzerland


Deep Level Transient Spectroscopy (DLTS) is often used to identify and quantify defects in semiconductors. In the DLTS spectrum of CIGS (CuInGaSe<sub>2</sub>) solar cells generally two types of signals are observed: one for which the capacitance transients are measured well below room temperature (RT) labeled N1, and a second corresponding to transients measured close to RT, N2. We have recently shown that the N1 signal can be related to a non-ideal contact in the solar cell [1].

In this work the N2 signal was investigated using isothermal DLTS (capacitance transients at constant voltage) and isothermal constant-capacitance DLTS (CC-DLTS, voltage transients at constant capacitance) experiments at RT. In CC-DLTS a non-exponential factor in the transients due to high trap concentrations is avoided. The effect of filling pulse duration ( $t_p$ ) on the N2 signal is studied here in detail.


Both the DLTS and CC-DLTS methods point to an anomalous filling behavior. From a certain  $t_p$  onwards a peak appears that shifts towards larger emission time as  $t_p$  increases. The relation between these results and the energy level diagram of the metastable In-on-Cu antisite defect is discussed. DLTS experiments with variation of  $t_p$  may help to understand the nature of the metastable defects causing the N2 signal.

[1] J. Lauwaert et al., Progr. Photovolt. 2012, in press.

### DLTS meting tb 0, 30, 60



### CC-DLTS tb0



### CC-DLTS tb 30 en 70s

