An experimental approach to study the effect of fire on flint tools

Éva Halbrucker¹, Géraldine Fiers², Hans Vandendriessche¹, Tim De Kock², Veerle Cnudde², Philippe Crombé¹

¹Prehistory Research Group, Department of Archaeology, Ghent University, Belgium

²Pore-scale Processes in Geomaterials Research Group (PProGress)/UGCT, Department of Geology, Ghent University, Belgium

INTRODUCTION & AIM

On prehistoric sites, burnt lithic artefacts are generally numerous, in particular in association with domestic hearths. These artefacts are often discarded from use-wear analysis, which potentially causes a bias in the functional interpretation of prehistoric sites.

Aim:

Experimental and semi-quantitative approach to study the effect of fire on different flint types and on different use-wear traces.

- How do physical and geochemical features of flint change during heating?
- How do these changes affect the preservation of use-wear traces?

METHODOLOGY: TEST FIRES AND GEOLOGICAL SAMPLES

Evaluation of different fuels

Fuels known from archaeological sites in NW Belgium:

- Pine wood: used in the Early Mesolithic
- Oak wood: used in the Late Mesolithic
- Bone: commonly found in hearths throughout Prehistory

▲ Test fire with mixed wood and bone: Left: photograph; Right: thermal image

Reproduction of different degrees of thermal alteration on flints

Flakes from geological samples are positioned at different distances from the center of the fire.

Temperature was monitored using a heat camera and IR thermometer.

▲ Fire of oak and pine wood with bones and flint samples: Left: photograph; Right: thermal image

METHODOLOGY: EXPERIMENTAL ARTEFACTS

▲ Flowchart of protocol for burning experiments of used tool replicas

▲ Fire with experimentally used artefacts; Left: documentation during experiment (heat camera and IR thermometer); Right: thermal image with indication of locations of visible artefacts

RESULTS: ARCHAEOLOGY

Microscopic photos of use-wear before and after burning

Visual alteration on flint when placed at different locations in the fire. Heavily (1), medium (2) and slightly (3) burnt samples are replicated.

RESULTS: BURNING CHARACTERISTICS

Fire characteristics

◀ Temporal plot of temperature during the fire with mixed wood and bones. At dashed line the max temperature was below 660°C (calibration setting of heat camera).

Flint alteration features

◀ Haubourdin flint before and after burning in the middle of the fire (microCT 3D rendering)

▲ Colour measurements before (grey) and after (coloured) heating in campfire. Note larger L* difference in samples closer to the centre of the fire

Contact:
Éva Halbrucker

Ghent University Department of Archaeology

Address: Sint-Pietersnieuwstraat 35 9000 Ghent, Belgium

✉ eva.halbrucker@ugent.be

🐦 @ArcheoUgent @halbevi

📘 Archeologie UGent

CONCLUSION

The developed methodology allows to study

- the different changes in flint during heating;
- the preservation of use-wear traces in different stages.

Thermal damage in campfire can be linked to maximum heating temperature by continuously monitoring the temperature.

The use-wear traces are still clearly recognisable on medium burnt pieces, these should be included in the functional analysis of archaeological assemblages.