Biochar from sawmill residues: Characterization and evaluation for its potential use in the horticultural growing media

Dilani Rathnayake ^{a*}, Hamish Creber ^b, Reinhart Van Poucke ^c, Saran Sohi ^b, Erik Meers ^c, Ondrej Masek ^b, Frederik Ronsse ^a

^a Thermochemical Conversion of Biomass Research Group, Department of Green Chemistry and Technology, Faculty of Bioscience Engineering, Gent University, 653, Coupure Links, 9000, Gent, Belgium.

^b UK Biochar Research Centre, School of GeoSciences, Crew Building, The King's Buildings, University of Edinburgh, EH9 3FF, Edinburgh, United Kingdom.

^c Laboratory of Analytical Chemistry and Applied Ecochemistry, Department of Green Chemistry and Technology, Faculty of Bioscience Engineering, Gent University, 653, Coupure Links, 9000, Gent, Belgium.

*Corresponding author: Dilani Rathnayake (<https://orcid.org/0000-0002-7904-246X>)

Full postal address of the corresponding author: Thermochemical Conversion of Biomass Research Group, Department of Green Chemistry and Technology, Faculty of Bioscience Engineering, Gent University, 653, Coupure Links, 9000, Gent, Belgium. (dilani.rathnayakemudiyanselage@UGent.be).

Highlights

- Sawmill byproduct was used to produce biochar
- Addition of biochar increased the pH, EC and nutrient content in the medium
- The inclusion of biochar in 25% to 50% volume ratio improved plant growth parameters compared to peat-only media
- Higher biochar proportions in the medium diminish the physico-chemical properties and plant growth parameters

Abstract

Peat remains the primary constituent of horticultural growing media in professional use. However, use of peat in horticultural growing media results in environmental problems such as greenhouse gas emissions due to excavation of natural peatlands. Biochar is gaining attention as a sustainable alternative to peat use in horticulture. This study examined the potential of biochar produced from sawmill residues as a partial alternative to peat in horticultural growing media. Five treatments including peat only, biochar only, biochar and peat in 1:1, 1:3, and 3:1 (V/V)

ratios were assessed. The addition of biochar into growing media increased the pH and EC of the medium. However, physical properties (air filled porosity and water holding capacity) were negatively affected with the increase in biochar content in the medium. According to the germination test results, biochar significantly improved germination and the shoot and root length of germinated seeds of cress, lettuce and tomato when compared to peat-only and biochar-only treatments. The inclusion of biochar in 25% to 50% volume ratio improved plant growth parameters compared to peat-only and biochar-only media. Results obtained from this study suggest that sawmill residues offer great potential as a feedstock for biochar production and inclusion of biochar has positive effects on seed germination and plant growth that might compete with modified peat. In terms of technical performance, biochar could effectively replace 25% to 50% of peat use in horticultural growing media without compromising growth performance.

Key words: Sawmill residue, Biochar, Peat replacement, Growing media, Germination

1. Introduction

Peat extracted for horticultural purposes rapidly oxidizes leading to the emission of the greenhouse gas CO₂ from previously-stored stocks of carbon in the natural environment (Sohi et al. 2013). Peatlands are wetland ecosystems characterized by the accumulation of organic matter and currently account for 3% of global land area (Robertson 1993; Alexander et al. 2008). Peatlands play an essential role in ecosystem services and contain one-third of soil carbon (C) stock (Page et al. 2011). Depending on human use, peatland can act as either C sink or C source (Kern et al. 2017). Current use of peat in horticulture involves around 11 million metric tons per year (Clarke and Rieley 2010; Bos et al. 2011). Finding sustainable substitutes for peat used in horticultural media has been recognized as a strategic option by the Dutch government to minimize negative impacts on peatlands resulting from unsustainable peat extraction (Bos et al. 2011).

Non-peat options for peat substitution need to meet several requirements: (i) they must be readily available and secure in supply (ii) have good quality and (iii) their sources and processing have to be sustainable. Above all, the economic viability is a key factor overlying these requirements (Sohi et al. 2013), as the cost of peat without including all externalities is very low. Several candidate materials are already recognized and in use for the replacement of peat in growing media (Barrett et al. 2016) such as compost, coir, bark and wood fiber, etc. However, these materials also have negative environmental impacts due to greenhouse gas emissions associated with processing and transport (Schmilewski 2008). Currently, these materials can be grouped into three categories based on their total carbon footprint associated with processing, handling and transportation: (i) coir (less than 500

kg CO₂e⁻¹ of C footprint) (ii) peat (from UK and Ireland) and perlite (500 to 750 CO₂e⁻¹ of C footprint) and (iii) peat (Finland), green compost, bark, wood fibre and vermiculite (more than 750 CO₂e⁻¹ of C footprint) (Defra 2009).

Biochar is increasingly getting attention as a partial peat substitute owing to certain attractive physical and chemical properties (Tian et al. 2012; Fornes et al. 2017). These properties include macro porosity that facilitates the retention and release of water, low bulk density, resistance to compression and shrinkage, the potential for manufacture in different specified particle size ranges and the possibility to improve microbial activity due to its internal pore structure (Shackley et al. 2010; Weber and Quicker 2018). Biochar is produced through slow pyrolysis which is the thermochemical conversion of biomass under an oxygen-limited atmosphere (Lehmann et al. 2006). Biochar itself is highly recalcitrant in the environment compared to raw feedstock material. It will only degrade slowly in the soil environment and help to sequester atmospheric CO₂ (Lehmann et al. 2006; Wu et al. 2020). Even though biochar has a lot of favorable properties as a non-peat substitute, the net effect on cost-effectiveness and environmental sustainability can only be positive if the production of biochar is sustainable (Sohi et al. 2013).

Biochar characteristics play an important role when used as a growing medium component (Huang and Gu 2019). When biochar is used in relatively larger proportions such as in horticultural growing media (compared to biochar use in e.g. agricultural soil amendment where its concentration in soil is typically few wt.% or less), biochar characteristics have significant impact on the growing medium's physicochemical properties and resulting plant growth (Nieto et al. 2016). Thus, proper characterization of biochar prior to application is essential to identify the optimal characteristics for the growing medium application as well as to maintain consistent quality of biochar over sequential production batches (Kern et al. 2017). Having a high carbon content in biochar increases the stability of the biochar and the growing medium (Kaudal et al., 2018; Rathnayake et al., 2020). Consequently, the biochar's microbial degradation over time is reduced as well as the greenhouse gas emissions (Lévesque et al. 2018).

Biochars with high pH could alleviate the complications associated with acidic pH in soil substrates and can substitute liming requirements (Margenot et al. 2018). Biochars produced from different feedstock materials at the same production temperature as well as biochars produced from the same feedstock material but under different pyrolysis temperatures could have considerably different pH values (Ronsse et al. 2013; Weber and Quicker 2018). For an example, the pH values of biochars produced from pruning waste at 300 °C and 500 °C were 7.53 and

10.30, respectively (Nieto et al. 2016). On the other hand, the pH values from biochars produced from mixed soft wood, greenhouse waste and poultry litter at 550 °C were 8.45, 9.65, and 9.51 respectively (Singh et al. 2017). Generally, biochars produced from high ash containing feedstocks and biochars produced at higher pyrolysis temperatures have higher pH (Blok et al. 2017). Moreover, depending on the biochar content in the growing medium, its effect on the resulting growing medium's pH could be varied (Kern et al. 2017; Huang and Gu 2019). For instance, the higher the biochar content in the medium, the higher the pH of the medium (Vaughn et al. 2013). Also, the magnitude of the changes in pH of the medium with different biochar rates is highly dependent on the biochar type, which is ultimately dependent on the feedstock composition and production temperature (Nieto et al. 2016). On the other hand, having a high ash content and high alkalinity could lead to phytotoxicity as well as nutrient unavailability and antagonistic effects on nutrient utilization (Rogovska et al. 2012; Reza et al. 2020). Finally, the presence of potentially toxic elements and organic compounds (i.e. volatile organic compounds and polyaromatic hydrocarbons) could adversely impact seed germination and plant growth (Munzuroglu and Geckil 2002; Buss et al. 2016).

In terms of physical biochar properties, the biochar particle size distribution affects structural properties (i.e., bulk density, water holding capacity and porosity etc.) and nutrient availability in the medium (Ferlito et al. 2020; Prasad et al. 2020). All these physical properties of the growing medium are heavily dependent on the production conditions (i.e. pyrolysis temperature and heating rate), the type of feedstock material used in biochar production and the biochar content in the medium (Ronsse et al. 2013; Antonangelo et al. 2019; Keskinen et al. 2019). For instance, water holding capacities of the growing media with 75% (v/v) and 50% (v/v) of pruning waste biochar produced at 300 °C were 38.63% and 40.54%, respectively (Nieto et al. 2016). On the other hand, for the same pruning waste feedstock material, biochar produced at 500 °C resulted 51.73% and 52.74% of water holding capacities when those biochars were incorporated in 75% (v/v) and 50% (v/v) in the growing medium, respectively (Nieto et al. 2016). Air filled porosity could be changed with the biochar type and its concentration used in the growing medium. For instance, Tian et al., (2012) reported an increase of air filled porosity (i.e., 15.28% to 21.55%) when green waste biochar content in the medium increased from 50% (v/v) to 100% (v/v). Moreover, that green waste biochar had higher quantity of particles over 2 mm compared to peat material used in their study and the increase in air filled porosity was linked to the improvement of the macro porosity of the medium due to these larger biochar particles (Tian et al. 2012). Thus, particle size distribution plays an important role in determining hydro-physical properties of the growing medium (Huang and Gu 2019).

In recent literature, biochar has been produced under various pyrolysis conditions from various waste feedstock sources and their potential to replace peat and peat based commercial growing media has been evaluated. According to those studies, paper sludge biochar was able to replace 50% of brown peat (Méndez et al., 2015), pruning waste biochar was able to replace 50-75% of brown peat (Nieto et al. 2016), green waste biochar was able to replace 50% of peat substrate (Tian et al. 2012), sugarcane biochar could replace 25-50% of peat based commercial growing media (Webber et al. 2018b), pine wood biochar could substitute 25-75% of peat based commercial growing media (Webber et al. 2018a), and wood biochar is able to substitute 20% of peat (Blok et al. 2017) without plant growth inhibition. Moreover, Tian et al., (2012) reported 20% of plant biomass gain after addition of 50% of biochar into the medium. Altland et al., (2017) reported that 15%-20% of rice hull biochar addition could increase the tomato shoot growth significantly due to favorable physico-chemical properties in the medium. In previous work, Blok et al., (2017) reported increased plant growth using different types of biochar at 20% (v/v) content in replacing peat in potting soil.

The wood processing industry, especially sawmills produce a range of byproducts, including a fraction that arises from ring debarking. This fraction is produced from the outer 1 cm of the harvested tree that is removed in the absence of dead bark (Arets et al. 2011). Until now, this vascular cambial zone (VCZ) material has been mainly used as a low-cost mulching material in agriculture, or locally burned for bioenergy generation. Due to high production volumes of VCZ material and its mineral nutrient composition, it can be used as a feedstock to produce VCZ biochar (Forest Research 2019). In the context of finding alternative uses for VCZ materials and finding a sustainable peat replacement, we examined biochar produced by slow pyrolysis of VCZ from Sitka spruce (*Picea sitchensis*). In addition to assessing the conversion of Sitka spruce VCZ to biochar, we also assessed the resulting biochar for physico-chemical properties relevant to its potential use in partial substitution of peat in horticultural growing media, and to validate partial peat substitution through germination and plant growth assays.

2. Materials and methods

2.1. VCZ biochar and peat

Production of biochar was carried out using the stage III continuously fed pyrolysis rotary kiln at the University of Edinburgh (Mašek et al. 2018). The feedstock was sourced from the Petersmuir sawmill, BSW Ltd, Scotland. The VCZ material was found to comprise 40% wood and 60% bark by volume, incorporating the vascular cambium. Whole feedstock material was derived from the sawmill residue produced from Sitka spruce (*Picea sitchensis*) logs during the process of ring debarking. Feedstock material was pyrolyzed at nominal highest

treatment temperature (HTT) of 550 °C. Feedstock material was heated at a rate of 78 °C/min and the residence time at HTT was 3.9 min. The peat used in this study was a commercial peat intended for use in vegetable seedling production which was obtained from Peltracom (Belgium) and which consisted of 70% neutralized white peat and 30% neutralized black peat of Latvian origin.

2.2. Biochar and peat characterization

2.2.1. C, H, N and S analysis

The C, H, N, S analysis of biochar and peat were performed in triplicates in a Flash 2000 Elemental Analyzer (Thermo Fisher Scientific, Waltham, MA, USA). The 2,5-bis(5-tert-butyl-benzoxazol-2-yl) thiophene (BBOT) was used as standard reference material during CHNS analysis.

2.2.2. Ash content, volatile matter content and fixed carbon content

Proximate analysis was carried out according to the method described in Singh et al. (2017). Briefly, the moisture content was determined by keeping the sample at 105 °C for 18 hours in a conventional oven. Then, oven dried weights of sample containing crucibles were recorded. Volatile matter content was determined by holding the sample containing crucibles (with the lid on) at 950 °C for 10 minutes in a muffle furnace. Ash content was determined after heating the sample containing, open crucibles at 750 °C for 6 hours in the muffle furnace.

2.3. Growing medium formulation

Five formulations were tested: biochar, peat and three biochar–peat mixtures (Table 1). All the biochar–peat mixtures were defined on a volume basis and implemented from homogeneous ingredients.

Table 1 Composition of growing medium formulation

Treatment	Composition (volume basis)
BC100	Biochar-only (100%)
BC75P25	Biochar (75%): peat (25%)
BC50P50	Biochar (50%): peat (50%)
BC25P75	Biochar (25%): peat (75%)
P100	Peat-only (100%)

2.4. Physical properties of the growing media

2.4.1. Particle size distribution

Particle size distribution of each medium was analyzed using 50 g of dry sample. An AS200 sieve analyzer (Retsch, AS 2000, Germany) was used to separate different particle size fractions by shaking for 15 minutes. The sieve sizes ranged from 0.075 mm to 4 mm. Duplicates were carried out for each treatment.

2.4.2. Structural properties

Dry bulk density, total pore space, air space and water holding capacity were determined using the method described in Nieto et al., (2016). Briefly, each substrate was filled into a container with a known volume which has sealed drainage holes at the bottom. Then, water was added until the medium got saturated while being put on a watertight pan. Then after saturating, the seal which covered the bottom hole was removed and the sample was allowed to freely drain overnight. The released water quantity was measured to calculate the air space percentage inside the medium. The medium and the container were subsequently weighed. After that, the medium inside the container was put into a pre-weighed pan and put into a drying oven at 105 °C for 24 hours. Then, the oven dried weight of the medium was used to calculate the water holding capacity of the medium. The total porosity of the medium was calculated by summing up the air space and water holding capacity. Dry bulk density was calculated by using oven dried mass of the medium divided by the container volume.

2.5. Chemical properties of the growing medium formulations

2.5.1. pH and EC and organic matter content

The pH and EC of biochar, peat and biochar and peat mixtures were measured in 1:10 (m/v) ratio with deionized water after shaking for 90 minutes and using an electrical conductivity electrode (WTW-LF537, Germany) and a pH meter (Model 520, Orion, Boston, MA, USA) according to the method described in Singh et al. (2017). Triplicates were analyzed for each mixture. In order to measure the organic matter content, 0.5 g of the oven dried (105 °C) material was weighed into a crucible of a known mass. The sub-sample was kept in the muffle furnace at 550 °C for 4 h. The mass loss on reweighing was taken as an estimate for organic matter content.

2.5.2. Elemental composition

The total nutrient content and potentially toxic elements in the biochar, peat and, biochar– peat mixtures were analyzed using the modified dry ashing method described in Singh et al. (2017). Briefly, finely ground peat and biochar samples were oven dried at 105 °C for 24 hours. Approximately 200 mg of sample was weighed into a digestion tube, and subsequently heated at 500 °C for 8 hours. After the samples cooled down to ambient air

temperature, the mass of the sample contained in the tube was recorded. The samples were then digested with 5 ml of concentrated (70%) HNO₃ (Chem-Lab, Zedelgem, Belgium) and evaporated until dry. After cooling, 1 ml of HNO₃ and 4 ml of H₂O₂ (30% VWR chemicals, Belgium) were added and evaporated to dryness. Finally 2 ml of HNO₃ was added to dissolve the solids. The resulting solution was filtered using Whatman no 41 filter paper and the filtrate was diluted to 50 ml with deionized water. The resultant solutions were analyzed using ICP-OES (Varian Vista MPX, Varian Palo Alto, California, USA) and ICP-MS (Varian Vista-MPX CCD Simultaneous, Varian Inc., Victoria, Australia) for K, Ca, Mg, Fe, Al, B, Mn, P, Cr, Co, Ni, Cu, Zn, As, Mo, Cd and Pb. Duplicate sub-samples were analyzed from each material.

2.6. Germination assay

In order to assess the phytotoxicity of the formulated growing media, a germination assay was conducted. Briefly, 10 seeds of three species were used: cress (*Lepidium sativum*) variety Common, lettuce (*Lactuca sativa*) variety Appia, and tomato (*Solanum lycopersicum*) variety St. Pierre. Seeds and media containing petri dishes were maintained at 25 °C for 3 days in an incubation chamber. The number of germinated seeds and shoot and root length of the germinated seeds were counted and recorded. The assay was applied with 10 replicates (10 seeds per replicate). Ratio of shoot length to root length of germinated seeds was expressed as germination index. Germination rate was calculated using following eq 1.

$$\text{Germination rate (\%)} = 100 * \frac{\text{Number of germinated seeds after 3 days}}{\text{Total number of seeds sowed}} \quad (\text{eq. 1})$$

2.7. Plant growth assay

A plant growth assay was conducted using tomato (*Solanum lycopersicum*) variety St. Pierre inside a laboratory growing chamber with controlled daylight for 12 hours. The experiment was carried out up to four weeks, to assess the suitability of the growing medium formulations to support early seedling growth. Five replicates per treatment were carried out in which 200 cm³ of each pot with a volume of 275 cm³ were filled. One seedling per pot was maintained throughout the plant growth assay. At the end of the four weeks after seeding, the number of leaves per seedling was recorded. After uprooting the seedlings, the fresh weight and lengths of both shoots and roots were measured. Fresh seedling samples were dried at 70 °C for 24 hours to determine the shoot and root dry weights of each seedling.

2.8. Statistical analysis

Both germination assay and preliminary plant growth assay were arranged in a completely randomized design. Statistical analyses were performed using Microsoft Excel 2016 and IBM's SPSS 22 software packages. Differences between the treatments were assessed using Tukey's post hoc test (at a significance level of 0.05) performed after a one-way ANOVA (analysis of variance).

3. Results and discussion

3.1. Properties of biochar and peat

The results from the basic chemical analysis of biochar and peat used in the experiments are shown in Table 2.

Table 2 Chemical properties of biochar and peat (means $\pm$ standard deviation, $n=3$). (dwb- dry weight basis).

Property	Unit	Biochar	Peat
Total C content	% (dwb)	68.0 ± 2.20	47.6 ± 1.52
Total H content	% (dwb)	2.0 ± 0.10	5.4 ± 0.11
Total N content	% (dwb)	0.5 ± 0.01	1.3 ± 0.05
C/N ratio	mol/mol	157.5 ± 1.65	41.2 ± 2.22
H/C ratio	mol/mol	0.4 ± 0.02	1.4 ± 0.02
Ash content	% (dwb)	9.0 ± 0.31	4.2 ± 0.02
Volatile matter content	% (dwb)	21.0 ± 2.12	70.5 ± 0.80
Fixed carbon content	% (dwb)	70.0 ± 2.43	25.3 ± 0.54

The bulk elemental ratio (ultimate analysis) results show higher total C content and lower total H and N content in biochar compared to peat. Pyrolysis involves the progressive elimination of H and O and relative enrichment in C. As the relative enrichment in C and depletion in hetero-elements like H and O is linked to biochar stability, the H/C ratio is widely used as an indicator of biochar stability (Crombie et al. 2013). Although the O/C ratio can fulfil a similar function, the O content is rarely determined directly, and H/C has been found a more sensitive indicator. Based on the molar H/C ratio (0.4 ± 0.02), the stability of biochar used in this study was considerably higher than the requirement (<0.70) proposed by the international research community (Budai et al. 2013; Schmidt et al. 2016). In contrast, the recalcitrance of peat is low relative to the H/C benchmark (1.4 ± 0.02). Fixed carbon measured in proximate analysis is considered to reflect the content of aromatic moieties in a substrate that are not readily

mineralized (Leng et al. 2019). It is also considered to provide an indication of relative stability (Crombie et al. 2013). The biochar used in this study had a fixed C content of $70 \pm 2.43\%$, indicating higher intrinsic stability. The stability of peat is comparatively low. Having material with higher stability in growing media could increase its resistance towards microbial degradation and lower the CO₂ emissions upon degradation (Blok et al. 2017; Lévesque et al. 2018).

Volatile matter shows the opposite pattern, considered to comprise the labile, readily mineralizable fraction of a substrate. The ash reflects the inorganic component with variable elemental composition (Crombie et al. 2013; Antonangelo et al. 2019). The ash includes some nutrient elements that can improve plant nutrition, but also potentially phytotoxic elements that inhibit plant growth (Singh et al. 2017). The higher ash content in biochar is indicative of a potentially higher nutrient content compared to peat (Weber and Quicker 2018). Proximate composition of biochar is therefore a feedstock dependent property as well as a reflection of pyrolysis conditions (Rathnayake et al. 2020b; Reza et al. 2020). Biochar in this study had a comparatively lower ash content ($9.0 \pm 0.31\%$) compared to biochars that are derived from grass or crop residues (20-30%) (Vassilev et al. 2010; Weber and Quicker 2018). The biochar has a low N content owing to the volatility of N under pyrolysis conditions. Consequently, biochar had a higher C/N ratio compared to fresh plant biomass and also the peat used in this study. Degradable plant residues with high C/N ratio can immobilize accessible nitrogen in soil, owing to the minimum requirement for N in microbial growth (Carter et al. 2013). Non-degradable C cannot result in this effect, but volatile C and chemical N sorption by biochar may impact plant N availability (Bhatta et al. 2016).

3.2. Growing medium physical properties

Particle size distribution of each substrate formulation used in this study is reported in Table 3. Particle size distribution affects the bulk density of a growing medium and in turn, the particle size of its constituents is relevant. The target bulk density for a growing medium depends on the plants to be grown, their containers (type and size), growing conditions (i.e. outdoor or indoor), type of irrigation, handling requirements, etc. (Barrett et al. 2016). Bulk density, air filled porosity, water holding capacity and total porosity are shown in Table 4. Reflecting the smaller sized particles provided by biochar, dry bulk density was much higher for BC100 (0.28 ± 0.02 g/cm³) than for P100 (0.15 ± 0.02 g/cm³). The differences in total porosity and air-filled porosity were proportionally similar, but inversely related to those of bulk density (total porosity of $49.18 \pm 0.18\%$ for BC100 compared to $84.42 \pm 0.59\%$ for P100; air filled porosity $4.81 \pm 0.43\%$ for BC100 compared to $13.71 \pm 0.15\%$ for P100). The difference in water holding capacity was proportionally greater: $70.72 \pm 0.45\%$ for P100 compared to $44.38 \pm 0.25\%$ for BC100. Particle size distribution (PSD) affects bulk density, water holding capacity and porosity of the growing

medium (Nemati et al. 2015). Coarse particles provide air voids while fine particles are associated with moisture retention (Landis et al. 2009). The particle size distribution has a huge impact on drainage and penetrability of a porous medium and makes up its texture (Blok et al. 2008). The texture of the medium determines the solute and gas flows inside the medium (Blok et al. 2017). The most desirable particle size fraction for a containerized growing medium is between 0.25 mm and 2 mm (Méndez et al., 2015). In the range of 0.25-2 mm, BC100 and P100 had the lowest and the highest amount of particles respectively. Addition of biochar reduced the amount of particles in the desirable size fraction. Although the biochar used in this study diminished the textural quality of the growing media, PSD is an adjustable property of biochar and can be tuned to requirements (Sohi et al. 2013).

Table 3 Percentage particle size distribution of growing medium formulations.

Particle size fraction (mm)	Average weight percentage (%)				
	BC100	BC75P25	BC50P50	BC25P75	P100
> 4	0.8	1.2	1.3	0.0	1.6
4 - 2	6.4	5.2	2.7	5.0	6.5
2 - 1	18.4	13.3	15.4	16.5	19.4
1 - 0.5	17.6	19.1	19.5	27.3	29.0
0.5 - 0.25	17.6	31.8	24.2	27.3	24.2
0.25 - 0.1	19.2	19.7	22.1	16.5	12.9
0.1- 0.075	13.2	8.1	8.7	3.3	2.4
< 0.075	6.8	1.7	6.0	4.1	4.0

The effect of increasing the biochar content on mixed formulations was not linear with respect to the physical parameters. This is probably because large pores in which smaller sized particles of denser biochar can reside depend on the abundance of the coarser peat ingredient (Wallach 2008). Biochar increased dry bulk density by 47% in BC50P50 compared to P100, but bulk density of BC75P25 was only 53% higher. Small-sized biochar particles located in other pores diminish porosity less than replacing peat with biochar. Nieto et al., (2016) also observed increase in bulk density after incorporation of pruning waste biochar into the growing medium. Air-filled porosity was 10% lower for BC50P50 compared to P100, but 51% lower for BC75P25 because of lower porosity in the basic ingredients. Dumroese et al., (2018) also reported a decrease of air filled porosity with the increase of wood biochar content in the medium. However, Nieto et al., (2016) observed increase and decrease of

air filled porosity in the medium when biochars produced at high temperature (500 °C) and produced at low temperature (300 °C) respectively. Moreover, that effect was noted when biochar content in the medium increased from 50% to 75% (v/v).

Table 4 Physical properties of growing medium formulations (mean $\pm$ SD, n=3). Same letters indicate no significant difference at $p < 0.05$ level along the columns.

Treatment	Dry bulk density (g/cm ³)	Air space (%)	Water holding capacity (%)	Total porosity (%)
BC100	0.28 $\pm$ 0.02 ^a	4.81 $\pm$ 0.43 ^d	44.38 $\pm$ 0.25 ^e	49.18 $\pm$ 0.18 ^e
BC75P25	0.23 $\pm$ 0.01 ^{ab}	6.68 $\pm$ 0.22 ^c	48.57 $\pm$ 0.36 ^d	55.24 $\pm$ 0.58 ^d
BC50P50	0.22 $\pm$ 0.01 ^b	12.34 $\pm$ 0.25 ^{ab}	54.26 $\pm$ 0.21 ^c	66.60 $\pm$ 0.46 ^c
BC25P75	0.18 $\pm$ 0.03 ^{bc}	11.14 $\pm$ 0.27 ^b	68.57 $\pm$ 0.06 ^b	79.71 $\pm$ 0.21 ^b
P100	0.15 $\pm$ 0.02 ^c	13.71 $\pm$ 0.15 ^a	70.72 $\pm$ 0.45 ^a	84.42 $\pm$ 0.59 ^a

Effects on water holding capacity depend on pore-size distribution and pore connectivity rather than directly on particle size (Edeh et al. 2020). Larger pores filled with porous small particles still exhibit porosity, but lower total pore volume and smaller pore size. Consequently, water holding capacity of peat–biochar mixtures decreased with higher biochar content, being 3% lower BC25P75 than for P100, 23% lower for BC50P50, and 31% lower for BC75P25. Nieto et al., (2016) observed a decrease of total porosity in the medium when biochar incorporated, compared to peat only control. Also, they observed slight increase of water holding capacity with the increase of biochar content in the medium from 50% to 75%. However, addition of biochar in both 50% and 75% level decreased the water holding capacity in the medium compared to peat only control.

Méndez et al., (2015) reported increase of bulk density, air filled porosity, water holding capacity and total porosity by 88%, 30%, 20% and 21% respectively after addition of 50% (volume basis) deinking sludge biochar into a peat based growing medium. On the other hand, Tian et al., (2012) observed increase in bulk density and water holding capacity by 23% and 1% and a decrease of total porosity and air filled porosity by 15% and 41% respectively, after addition of 50% of green waste biochar into peat based growing media. According to Méndez et al., (2015), the most desirable values for water holding capacity, air filled porosity and total porosity are 60-100%, 10-30% and 50-80% respectively. BC25P75, BC50P50 and P100 treatments in our study are in the optimum range for air filled porosity. Only P100 and BC25P75 are in the optimum range of the water holding capacity. Except BC100, all the

other treatments are in the optimum range for the total porosity. BC25P75 and P100 fall within the optimum range for all these parameters.

3.3. Growing medium chemical properties

The initial pH, EC and organic matter content of the substrate formulations are listed in Table 5. P100 had relatively higher organic matter (OM) content than the BC100. Thus, OM content in growing medium increases with the peat content. As peat is made of accumulated organic materials, peat has higher organic matter content (94-99%) (Girkin et al. 2019). Even though biochar had a higher total carbon content and fixed carbon content than peat used in this study, lower organic matter content compared to peat was observed. Additionally, the biochar used in this study had a higher ash content than the peat as well. The apparent contradiction in organic matter content and carbon content may be due to the difference in chemical composition of the organic matter in peat and biochar. During pyrolysis, most of the organic materials present in the feedstock convert into chemically more aromatic forms (thus more C rich, while lower in H and O content compared to the feedstock). Thus, biochar could have higher carbon content and fixed carbon contents. Having higher organic matter content in a growing medium is essential for improving water holding capacity and nutrient retention (van der Wal and de Boer 2017).

Typical growing media exhibit pH in the range of 5.5 to 6.5, and exhibit EC less than of 1 mS/cm (Blok et al. 2008; Barrett et al. 2016). Addition of biochar to the medium increased the alkalinity of the medium and only P100 and BC25P75 fall within the optimum pH range for growing media. The alkalinity of biochar depends largely on the amount and composition of its ash, which is in turn is a function of the feedstock material and the extent of mass reduction during pyrolysis, particularly affected by temperature (Dumroese et al., 2011). The presence of excessive salts is liable to damage seed germination and early stage growth through an increase in osmotic pressure (Mumme et al. 2018). On the other hand, plant uptake of key nutrients is pH-sensitive and liming agents are typically required to raise the pH of peat-based growing media to optimal levels. Alkaline biochar has a potential to mitigate the requirement for liming materials and mitigate the typical downward drift of pH that occurs in the growing media over time (Kern et al. 2017). In short, the balance in content of nutrient elements versus nutrient- and non-nutrient saline and/or alkaline elements will determine the benefits of including biochar in growing media. Optima may be hard to achieve without flexibility in feedstock and processing options (Margenot et al. 2018).

In previous work, Blok et al., (2017) advised that biochar with high nutrient content could result in salinity and alkalinity issues in growing media and feedstock with lower nutrient content should be preferred and used for pH adjustment in growing media containing acidic peat. Other studies have already reported the potential for biochar

to increase the pH and EC of the medium (Steiner and Harttung 2014; Nieto et al. 2016). Biochar had significantly higher macro and micronutrient content compared to peat (Table 6). The macro and micronutrient content of the growing medium increased with biochar content. Proper plant growth depends on the correct balance of available plant nutrients in the growing medium to avoid deficiencies while avoiding toxicity or antagonistic effects. The ratio of macro and micronutrients in biochar is entirely dependent on the ash composition of the biomass feedstock, their concentration and biochar alkalinity (relative to peat) affects their availability to plants (Blok et al. 2017; Antonangelo et al. 2019). The results in Table 6 show the initial nutrient content of the growing medium formulations, which is relevant to early stage plant growth. Such potentially positive effects on macro and micronutrient content resulting from mixing biochar and peat were also previously reported by Gaskin et al., (2008).

Table 5 pH, electrical conductivity (EC) and organic matter (OM) content of growing medium formulations (mean $\pm$ SD, n=3) Same letters indicate no significant difference at $p < 0.05$ level along the columns.

Treatment	pH	EC (mS/cm)	OM (%)
BC100	9.9 ± 0.1^a	0.4 ± 0.11^a	93.3 ± 1.54^a
BC75P25	9.5 ± 0.0^a	0.3 ± 0.13^a	93.6 ± 2.89^a
BC50P50	7.1 ± 0.2^b	0.2 ± 0.01^a	94.7 ± 2.65^a
BC25P75	5.9 ± 1.2^b	0.2 ± 0.03^a	95.9 ± 3.31^a
P100	5.6 ± 0.5^b	0.2 ± 0.02^a	97.9 ± 1.36^a

Elemental analysis does not confirm increased nutrient availability however, since this is affected by pH and the effects of physical properties on the availability of water in the medium. Although BC100 had the highest initial nutrient content of the tested media, a combination of sub-optimal EC, pH and PSD were liable to affect its potential benefits to plant growth as shown in previous studies (Nieto et al. 2016; Margenot et al. 2018). Since the elemental ratios in ash are fixed and the concentration of ash increases during pyrolysis, the possibility for toxicity to disturb or restrict metabolic functions must be considered (Hoover 2018). In this study neither peat nor biochar displayed concentrations of potentially toxic elements (PTEs) in excess of those proposed by IBI or EBC (Budai et al. 2013; Schmidt et al. 2016). The biochar had higher concentrations of Cr and Zn compared to peat (Table 7).

359 **Table 6** Initial micronutrient and macronutrient concentrations (mg/kg) for each growing medium formulation (mean $\pm$ SD, n=3). Same letters indicate no significant difference
 360 at $p < 0.05$ level along the columns.

Treatment	Mg	P	K	Ca	Fe	Mn	Cu	Zn
BC100	1364.7 $\pm$ 137.5 ^a	673.2 $\pm$ 101.7 ^a	2193.1 $\pm$ 284.6 ^{bc}	12995.3 $\pm$ 1805.9 ^a	500.6 $\pm$ 11.3 ^a	56.6 $\pm$ 6.8 ^a	3.9 $\pm$ 0.5 ^a	43.9 $\pm$ 2.4 ^{ab}
BC75	1342.4 $\pm$ 82.1 ^a	651.1 $\pm$ 51.4 ^a	2704.2 $\pm$ 52.2 ^a	14207.4 $\pm$ 329.8 ^a	459.9 $\pm$ 32.3 ^a	54.9 $\pm$ 3.2 ^a	5.1 $\pm$ 0.6 ^a	42.1 $\pm$ 1.4 ^b
BC50	1398.7 $\pm$ 72.2 ^a	614.8 $\pm$ 30.7 ^a	2570.4 $\pm$ 76.8 ^{ab}	12041.3 $\pm$ 242.5 ^a	441.1 $\pm$ 77.6 ^a	50.6 $\pm$ 2.7 ^a	4.2 $\pm$ 0.2 ^a	47.9 $\pm$ 1.4 ^a
BC25	1051.6 $\pm$ 48.4 ^b	318.9 $\pm$ 16.3 ^b	1888.1 $\pm$ 30.9 ^c	7341.1 $\pm$ 227.5 ^b	296.4 $\pm$ 34.1 ^b	29.7 $\pm$ 0.1 ^b	4.3 $\pm$ 0.7 ^a	30.4 $\pm$ 1.2 ^c
P100	685.2 $\pm$ 3.6 ^c	106.7 $\pm$ 1.6 ^c	192.2 $\pm$ 2.6 ^d	3225.1 $\pm$ 6.5 ^c	325.5 $\pm$ 19.7 ^b	11.1 $\pm$ 0.3 ^c	4.9 $\pm$ 0.1 ^a	28.7 $\pm$ 0.5 ^c

361
 362 **Table 7** Potentially toxic element concentrations (mg/kg) for each growing medium formulation (mean $\pm$ SD, n=3). Same letters indicate no significant difference at $p < 0.05$
 363 level along the columns.

Treatment	Al	Cr	Co	Ni	As	Mo	Cd	Pb
BC100	211.8 $\pm$ 27.3 ^b	3.9 $\pm$ 0.3 ^a	0.3 $\pm$ 0.0 ^a	1.9 $\pm$ 0.1 ^{bc}	0.4 $\pm$ 0.1 ^a	0.5 $\pm$ 0.0 ^b	0.02 $\pm$ 0.0 ^b	2.7 $\pm$ 0.4 ^a
BC75	291.8 $\pm$ 43.4 ^{ab}	3.1 $\pm$ 0.3 ^{ab}	0.3 $\pm$ 0.0 ^a	3.6 $\pm$ 1.1 ^a	0.3 $\pm$ 0.1 ^a	0.7 $\pm$ 0.1 ^a	0.02 $\pm$ 0.0 ^b	2.5 $\pm$ 0.1 ^a
BC50	363.7 $\pm$ 84.7 ^a	3.2 $\pm$ 0.6 ^{ab}	0.3 $\pm$ 0.1 ^a	2.4 $\pm$ 0.3 ^{ab}	0.3 $\pm$ 0.0 ^a	0.6 $\pm$ 0.1 ^{ab}	0.03 $\pm$ 0.0 ^b	2.9 $\pm$ 0.1 ^a
BC25	272.2 $\pm$ 27.6 ^{ab}	2.2 $\pm$ 0.3 ^b	0.2 $\pm$ 0.0 ^b	1.8 $\pm$ 0.2 ^{bc}	0.3 $\pm$ 0.0 ^a	0.3 $\pm$ 0.0 ^c	0.03 $\pm$ 0.0 ^b	1.8 $\pm$ 0.4 ^b
P100	364.3 $\pm$ 19.6 ^a	0.9 $\pm$ 0.2 ^c	0.1 $\pm$ 0.0 ^b	0.9 $\pm$ 0.1 ^c	0.3 $\pm$ 0.0 ^a	0.2 $\pm$ 0.0 ^c	0.09 $\pm$ 0.0 ^a	2.6 $\pm$ 0.01 ^a

364

365

3.4. Seed germination

Results of the germination assay are shown in Fig. 1. Germination assays can be used to evaluate the phytotoxicity of the growing medium formulations. Cress, lettuce and tomato seeds are used in most of the past studies due to their higher growth response and sensitivity to phytotoxic substances. Both promotion and inhibition of seed germination after mixing with biochar was observed by other studies (Margenot et al. 2018; Mumme et al. 2018; Rathnayake et al. 2021). In our study, lettuce, germination rate was 6% higher in BC75P25 and BC25P75 treatments compared to P100. BC50P50 and BC100 had the highest germination rate (19% and 13% increase respectively) for lettuce compared to other treatments. For tomato, BC50P50 exhibited 17% higher germination rate compared to peat while B100 revealed 7% reduction of germination rate. However, cress, tomato and lettuce seeds did not show any significant difference in germination rate among the treatments. Higher volatile matter content, higher ash content, and higher alkalinity in biochar could adversely impact seed germination due to the salt stress and disruption of cell metabolic pathways (Torbaghan 2012; Pavel et al. 2013; Dalias et al. 2018; Intani et al. 2019). Furthermore, phytotoxicity of biochar could arise from volatile organic compounds associated with the biochar arising from post-handling etc. (Buss and Masek 2014). Finally, metal stress imposed by potentially toxic elements could contribute to the inhibition of seed germination which depends on the seed structure (seed coating etc.) and plant species (Munzuroglu and Geckil 2002).

Shoot and root lengths of the germinated seeds were significantly different among plant species and treatments. For cress, BC50P50 and BC75P25 showed 19% and 10% increment in shoot length compared to P100. However, BC100 and BC25P75 showed 40% and 23% reduction in shoot length compared to P100. Lettuce shoot length was 7% lower for BC25P75 compared to P100. On the other hand, all the other treatments exhibited an increase of the shoot length in germinated lettuce seeds (71%, 58% and 67% in BC50P50, BC75P25 and BC100 respectively). For tomato, BC75P25 and BC50P50 treatments had highest shoot lengths in germinated seeds compared to P100 (240% and 258% increase in BC75P25 and BC50P50 respectively). Root length is a key indicator for the initial establishment phase of seedlings in growing media (Landis et al. 2009; Ferlito et al. 2020). Root lengths of the germinated seeds were significantly higher in BC50P50 treatment compared to P100. That was 69%, 121% and 146% increase in cress, lettuce and tomato seeds respectively. This may be due to the combined effect of P content and physico-chemical properties in BC75P25 and BC50P50 treatments compared to the P100 and B25P75 treatments. Even though, BC100 had the highest P content, the overall effect on root elongation could negatively affect from the poor physical properties in the medium due to the low porosity (Table 4). The germination index was also higher for BC100 than for P100 or any of the formulated mixes.

396

397 **Fig. 1** Shoot length, root length, shoot to root length ratio and germination rate of germinated seeds of cress, lettuce and tomato (mean $\pm$ SD, n=100). Same letters indicate no
 398 significant difference at $p<0.05$ level.

There is a variation in germination index across the media, with greater shoot length in BC75P25 and BC50P50. Shoot length increased for lettuce seeds when biochar content exceeded 25%. Several studies also reported the positive effects of biochar on seed germination (Gravel et al. 2013; Hoover 2018). However, soluble phytotoxic compounds have previously been implicated in inhibited germination and root and shoot growth of germinated seeds (Buss and Masek 2014).

3.5. Preliminary plant growth

Growth of tomato plants over 4 weeks was greater for the peat–biochar formulations than for P100, but P100 performed better than BC100 (Table 8). Number of leaves was 25% higher in BC25P75 and 25% lower in B100 compared to P100. In terms of shoot length, only BC25P75 and BC50P50 showed an increase of shoot length (19% and 25% in BC25P75 and BC50P50 respectively). Shoot length was 14% and 43% lower compared to P100 in BC75P25 and BC100 respectively. BC25P75, BC50P50 and BC75P25 showed 46%, 47% and 26% gain in root length compared to P100. Tomato can resist higher proportions of biochar in the medium due to its resistivity towards salinity (Dumroese et al. 2018). However, BC100 showed 33% lower root length compared to P100. This may be due to the poor physico-chemical properties in the BC100 (Table 4). Shoot dry weight was increased by 44% in BC25P75 and BC50P50 compared to P100. On the other hand, BC75P25 and B100 showed 18% and 61% reduction in root dry weight compared to P100. Based on shoot and root lengths, BC50P50 and BC25P75 showed the best performance. This result was reflected in shoot and root dry weight which was higher for BC50P50 and BC25P75 compared to all other media formulations. This may be due to the favorable physical properties such as air filled porosity and water holding capacities in BC25P75 and BC50P50 compared to other treatments.

Table 8 Plant growth parameters obtained through preliminary plant growth assay with tomato (mean $\pm$ SD, n=5). Same letters indicate no significant difference at $p < 0.05$ level.

Treatment	No. of leaves	Shoot length (cm)	Root length (cm)	Shoot dry weight (mg) d.b	Root dry weight (mg) d.b
BC100	3.0 $\pm$ 1.00 ^a	4.6 $\pm$ 0.50 ^c	5.1 $\pm$ 1.40 ^b	7.7 $\pm$ 2.01 ^c	2.8 $\pm$ 0.90 ^b
BC75P25	4.0 $\pm$ 0.00 ^a	6.9 $\pm$ 1.00 ^b	9.6 $\pm$ 1.21 ^a	28.4 $\pm$ 7.91 ^{bc}	5.9 $\pm$ 0.91 ^{ab}
BC50P50	4.0 $\pm$ 1.00 ^a	10.0 $\pm$ 0.90 ^a	11.2 $\pm$ 0.90 ^a	81.0 $\pm$ 12.50 ^a	10.3 $\pm$ 1.30 ^a
BC25P75	4.0 $\pm$ 1.00 ^a	9.5 $\pm$ 1.10 ^a	11.1 $\pm$ 2.01 ^a	73.3 $\pm$ 21.12 ^a	10.4 $\pm$ 4.41 ^a
P100	4.0 $\pm$ 0.00 ^a	8.0 $\pm$ 0.71 ^{ab}	7.6 $\pm$ 1.50 ^{ab}	58.0 $\pm$ 7.71 ^{ab}	7.2 $\pm$ 2.10 ^{ab}

The adverse effect of using only biochar has also been reported (Nieto et al. 2016). The harvested seedlings were not chemically analyzed to assess nutrient uptake and the pH and EC of the media at the end of the assay. Based on the other analyses conducted (pH, EC, elemental composition and germination assay) it may be inferred that the nutrient status, pH and EC were positively affected by biochar in the formulated mixes. Although Table 4 highlights potential for negative effects arising from the physical/structural properties of biochar, these may not have been accentuated under the controlled conditions of the study. In formulations where biochar was in a high proportion of a growing medium these negative effects may have become more apparent (Dumroese et al. 2011).

4. Conclusions

This study assessed the potential of VCZ biochar produced from sawmill residues to replace peat use in horticulture. The partial replacement of biochar in peat increased tomato plant growth compared to pure peat and pure biochar as growing media, as well as germination of tomato, lettuce, and cress seeds. At higher biochar contents in biochar-peat media, air-filled porosity and water holding capacity of the medium decreased. However, physical property values are within the optimum range for the growing media. The effects of biochar at contents of 25% and 50% by volume were positive in terms of macronutrients and not negative concerning pH or EC when compared to peat. These effects outweighed potentially adverse effects on physical properties, at least under the controlled moisture conditions used in this study. The foundation laid by this study can help in consecutive investigation of the use of VCZ biochar in horticultural growing media for optimizing plant growth under different agronomic conditions. Moreover, replacing peat by biochar will reduce the pressure on peatlands due to unsustainable horticultural peat extractions.

Declaration

Acknowledgements - The authors gratefully thank all reviewers for their comments and suggestions in improving the manuscript.

Funding - The study reported here received financial support from the European Union Horizon 2020 Research and Innovative Training Network programme under the Marie Skłodowska-Curie grant agreement No 721991. In addition, H. Creber received financial support from the E4 Doctoral Training Partnership of the Natural Environment Research Council in the UK.

Conflict of interest - The authors declare that they have no conflict of interest.

Ethics approval and consent to participate - Not applicable

Consent for publication - Not applicable

Availability of data and materials - All data generated or analysed during this study are included in this article.

References

- Alexander PD, Bragg NC, Meade R, et al (2008) Peat in horticulture and conservation: the UK response to a changing world. *Mires Peat* 3:
- Altland JE, Locke JC, Altland JE, Locke JC (2017) High rates of gasified rice hull biochar affect geranium and tomato growth in a soilless substrate. *J Plant Nutr* 40:1816–1828.
<https://doi.org/10.1080/01904167.2016.1249800>
- Antonangelo JA, Zhang H, Sun X, Kumar A (2019) Physicochemical properties and morphology of biochars as affected by feedstock sources and pyrolysis temperatures. *Biochar* 1:325–336.
<https://doi.org/10.1007/s42773-019-00028-z>
- Arets EJMM, Van der Meer PJ, Verwer CC, et al (2011) Global Wood Production. Assessment of industrial round wood supply from forest management systems in different global regions. Alterra Report- Wageningen UR 1808:79
- Barrett GE, Alexander PD, Robinson JS, Bragg NC (2016) Achieving environmentally sustainable growing media for soilless plant cultivation systems – A review. *Sci Hortic (Amsterdam)* 212:220–234.
<https://doi.org/10.1016/j.scienta.2016.09.030>
- Bhatta B, Chen D, Babu D, et al (2016) Biomass and Bioenergy An examination of physical and chemical properties of urban biochar for use as growing media substrate. *Biomass and Bioenergy* 84:49–58.
<https://doi.org/10.1016/j.biombioe.2015.11.012>
- Blok C, De Kreij C, Baas R, Wever G (2008) Analytical methods used in soilless cultivation, 1st edn. Elsevier Ltd.
- Blok C, Van der Salm C, Hofland-Zijlstra J, et al (2017) Biochar for horticultural rooting media improvement: evaluation of biochar from gasification and slow pyrolysis. *Agronomy* 7:.
<https://doi.org/10.3390/agronomy7010006>
- Bos MG, Diemont WH, Verhagen A (2011) Sustainable peat supply chain : report of the ad hoc working group enhancing the sustainability of the peat supply chain for the Dutch horticulture. Alterra Report-

476 Wageningen UR 2167:

477 Budai A, Zimmerman AR, Cowie AL, et al (2013) Biochar Carbon Stability Test Method : An assessment of
 478 methods to determine biochar carbon stability. *Int Biochar Initiative* 1–10

479 Buss W, Graham MC, Shepherd JG, Mašek O (2016) Risks and benefits of marginal biomass-derived biochars
 480 for plant growth. *Sci Total Environ* 569–570:496–506. <https://doi.org/10.1016/j.scitotenv.2016.06.129>

481 Buss W, Masek O (2014) Mobile organic compounds in biochar e A potential source of contamination e
 482 Phytotoxic effects on cress seed (*Lepidium sativum*) germination. *J Environ Manage* 137:111–119.
 483 <https://doi.org/10.1016/j.jenvman.2014.01.045>

484 Carter S, Shackley S, Sohi S, et al (2013) The Impact of Biochar Application on Soil Properties and Plant
 485 Growth of Pot Grown Lettuce (*Lactuca sativa*) and Cabbage (*Brassica chinensis*). *Agronomy* 3:404–418.
 486 <https://doi.org/10.3390/agronomy3020404>

487 Clarke D, Rieley J (2010) Strategy for Responsible Peatland Management, 6th Editio. International Peatland
 488 Society

489 Crombie K, Mašek O, Sohi SP, et al (2013) The effect of pyrolysis conditions on biochar stability as determined
 490 by three methods. *GCB Bioenergy* 5:122–131. <https://doi.org/10.1111/gcbb.12030>

491 Dalias P, Prasad M, Mumme J, et al (2018) Journal of Environmental Chemical Engineering Low-cost post-
 492 treatments improve the efficiency of hydrochar as peat replacement in growing media. *J Environ Chem Eng*
 493 6:6647–6652. <https://doi.org/10.1016/j.jece.2018.10.042>

494 Defra (2009) A preliminary assessment of the greenhouse gases associated with growing media materials. 1–30.
 495 https://doi.org/http://randd.defra.gov.uk/Document.aspx?Document=IF0154_9283_FRP.pdf

496 Dumroese RK, Heiskanen J, Englund K, Tervahauta A (2011) Pelleted biochar : Chemical and physical
 497 properties show potential use as a substrate in container nurseries. *Biomass and Bioenergy* 35:2018–2027.
 498 <https://doi.org/10.1016/j.biombioe.2011.01.053>

499 Dumroese RK, Pinto JR, Heiskanen J, et al (2018) Biochar can be a suitable replacement for Sphagnum peat in
 500 nursery production of *Pinus ponderosa* seedlings. *Forests* 9:. <https://doi.org/10.3390/f9050232>

501 Edeh IG, Mašek O, Buss W (2020) A meta-analysis on biochar’s effects on soil water properties – New insights
 502 and future research challenges. *Sci Total Environ* 714:. <https://doi.org/10.1016/j.scitotenv.2020.136857>

503 Ferlito F, Torrisi B, Allegra M, et al (2020) Evaluation of conifer wood biochar as growing media component for
504 citrus nursery. *Appl Sci* 10:. <https://doi.org/10.3390/app10051618>

505 Forest Research (2019) Tree bark biochar: a green bullet for Scotland's carbon store.
506 <https://www.forestresearch.gov.uk/news/tree-bark-biochar-a-green-bullet-for-scotlands-carbon-store/>

507 Fornes F, Belda RM, Córdova F De, Cebolla-cornejo J (2017) Assessment of biochar and hydrochar as minor to
508 major constituents of growing media for containerized tomato production. *J Sci Food Agric* 97:3675–3684.
509 <https://doi.org/10.1002/jsfa.8227>

510 Gaskin J., Steiner C, Harris K, et al (2008) Effect of Low-Temperature Pyrolysis Conditions on Biochar for
511 Agricultural Use. *Trans ASABE* 51:2061–2069. <https://doi.org/10.13031/2013.25409>

512 Girkin NT, Vane CH, Cooper H V., et al (2019) Spatial variability of organic matter properties determines
513 methane fluxes in a tropical forested peatland. *Biogeochemistry* 142:231–245.
514 <https://doi.org/10.1007/s10533-018-0531-1>

515 Gravel V, Dorais M, Ménard C (2013) Organic potted plants amended with biochar: Its effect on growth and
516 *Pythium* colonization. *Can J Plant Sci* 93:1217–1227. <https://doi.org/10.4141/CJPS2013-315>

517 Hoover BK (2018) Herbaceous perennial seed germination and seedling growth in biochar-amended propagation
518 substrates. *HortScience* 53:236–241. <https://doi.org/10.21273/HORTSCI12624-17>

519 Huang L, Gu M (2019) Effects of biochar on container substrate properties and growth of plants—a review.
520 *Horticulturae* 5:1–25. <https://doi.org/10.3390/horticulturae5010014>

521 Intani K, Latif S, Islam S, Müller J (2019) Phytotoxicity of Corn cob Biochar before and after Heat Treatment
522 and Washing. *Sustainability* 11:30. <https://doi.org/https://doi.org/10.3390/su11010030>

523 Kaudal BB, Aponte C, Brodie G (2018) Biochar from biosolids microwaved-pyrolysis : Characteristics and
524 potential for use as growing media amendment. *J Anal Appl Pyrolysis* 130:181–189.
525 <https://doi.org/10.1016/j.jaap.2018.01.011>

526 Kern J, Tammeorg P, Shanskiy M, et al (2017) Synergistic use of peat and charred material in growing media –
527 an option to reduce the pressure on peatlands ? *J Environ Eng Landsc Manag* 6897:.
528 <https://doi.org/10.3846/16486897.2017.1284665>

529 Keskinen R, Hyväluoma J, Sohlo L, et al (2019) Fertilizer and soil conditioner value of broiler manure biochars.

530 Biochar 1:259–270. <https://doi.org/10.1007/s42773-019-00020-7>

531 Landis TD, Jacobs DF, Wilkinson KM, Luna T (2009) Growing Media. In: Nursery Manual for Native Plants: A
 532 Guide for Tribal Nurseries. USDA, Forest Service, pp 100–121

533 Lehmann J, Gaunt J, Rondon M (2006) Bio-char sequestration in terrestrial ecosystems - A review. *Mitig Adapt*
 534 *Strateg Glob Chang* 11:403–427. <https://doi.org/10.1007/s11027-005-9006-5>

535 Leng L, Xu X, Wei L, et al (2019) Biochar stability assessment by incubation and modelling: Methods,
 536 drawbacks and recommendations. *Sci Total Environ* 664:11–23.
 537 <https://doi.org/10.1016/j.scitotenv.2019.01.298>

538 Lévesque V, Rochette P, Ziadi N, et al (2018) Mitigation of CO₂, CH₄ and N₂O from a fertigated horticultural
 539 growing medium amended with biochars and a compost. *Appl Soil Ecol* 126:129–139.
 540 <https://doi.org/10.1016/j.apsoil.2018.02.021>

541 Margenot AJ, Griffin DE, Alves BSQ, et al (2018) Substitution of peat moss with softwood biochar for soil-free
 542 marigold growth. *Ind Crops Prod* 112:160–169. <https://doi.org/10.1016/j.indcrop.2017.10.053>

543 Mašek O, Buss W, Roy-Poirier A, et al (2018) Consistency of biochar properties over time and production
 544 scales: A characterisation of standard materials. *J Anal Appl Pyrolysis* 132:200–210.
 545 <https://doi.org/10.1016/j.jaap.2018.02.020>

546 Méndez A, Paz-ferreiro J, Gil E, Gascó G (2015) The effect of paper sludge and biochar addition on brown peat
 547 and coir based growing media properties. *Sci Hortic (Amsterdam)* 193:225–230.
 548 <https://doi.org/10.1016/j.scienta.2015.07.032>

549 Mumme J, Getz J, Prasad M, et al (2018) Toxicity screening of biochar-mineral composites using germination
 550 tests. *Chemosphere* 207:91–100. <https://doi.org/10.1016/j.chemosphere.2018.05.042>

551 Munzuroglu O, Geckil H (2002) Effects of Metals on Seed Germination, Root Elongation, and Coleoptile and
 552 Hypocotyl Growth in *Triticum aestivum* and *Cucumis sativus*. *Arch Environ Contam*
 553 *Toxicol* 213:203–213. <https://doi.org/10.1007/s00244-002-1116-4>

554 Nemati MR, Simard F, Fortin J-P, Beaudoin J (2015) Potential Use of Biochar in Growing Media. *Vadose Zo J*
 555 14:1–8. <https://doi.org/10.2136/vzj2014.06.0074>

556 Nieto A, Gascó G, Paz-ferreiro J, et al (2016) The effect of pruning waste and biochar addition on brown peat

557 based growing media properties. *Sci Hortic (Amsterdam)* 199:142–148.
558 <https://doi.org/10.1016/j.scienta.2015.12.012>

559 Page SE, Rieley JO, Banks CJ (2011) Global and regional importance of the tropical peatland carbon pool. *Glob*
560 *Chang Biol* 17:798–818. <https://doi.org/10.1111/j.1365-2486.2010.02279.x>

561 Pavel VL, Sobariu DL, Diaconu M, et al (2013) Effects of heavy metals on *Lepidium sativum* germination and
562 growth. *Environ Eng Manag* 12:. <https://doi.org/10.30638/eemj.2013.089>

563 Prasad M, Chrysargyris A, McDaniel N, et al (2020) Plant nutrient availability and pH of biochars and their
564 fractions, with the possible use as a component in a growing media. *Agronomy* 10:1–17.
565 <https://doi.org/https://doi.org/10.3390/agronomy10010010>

566 Rathnayake D, Ehidihamhen P, Eugene C, et al (2021) Investigation of biomass and agricultural plastic co-
567 pyrolysis: Effect on biochar yield and properties. *J Anal Appl Pyrolysis*.
568 <https://doi.org/10.1016/j.jaap.2021.105029>

569 Rathnayake D, Maziarka P, Ghysels S, et al (2020a) How to trace back an unknown production temperature of
570 biochar from chemical characterization methods in a feedstock independent way. *J Anal Appl Pyrolysis*.
571 <https://doi.org/10.1016/j.jaap.2020.104926>

572 Rathnayake D, Rego F, Poucke R Van, et al (2020b) Chemical stabilization of Cd contaminated soil using fresh
573 and aged wheat straw biochar. *Environ Sci Pollut Res*

574 Reza MS, Afroze S, Bakar MSA, et al (2020) Biochar characterization of invasive *Pennisetum purpureum* grass:
575 effect of pyrolysis temperature. *Biochar* 2:239–251. <https://doi.org/10.1007/s42773-020-00048-0>

576 Robertson RA (1993) Peat , horticulture and environment. *Biodivers Conserv* 547:541–542

577 Rogovska N, Laird D, Cruse RM, et al (2012) Germination Tests for Assessing Biochar Quality. *J Environ Qual*
578 41:1014–1022. <https://doi.org/10.2134/jeq2011.0103>

579 Ronsse F, Van Hecke S, Dickinson D, Prins W (2013) Production and characterization of slow pyrolysis
580 biochar : influence of feedstock type and pyrolysis conditions. *Gcb Bioenergy* 5:104–115.
581 <https://doi.org/10.1111/gcbb.12018>

582 Schmidt HP, Bucheli T, Kammann C, et al (2016) European biochar certificate-guidelines for a sustainable
583 production of biochar

584 Schmilewski G (2008) The role of peat in assuring the quality of growing media. *Mires Peat* 3:

585 Shackley S, Sohi S, Brownsort P, et al (2010) An assessment of the benefits and issues associated with the
586 application of biochar to soil. 1–132

587 Singh B, Camps-Arbestain M, Lehmann J (2017) *Biochar: A Guide to Analytical Methods*. Csiro Publishing

588 Sohi S, Gaunt J, Atwood J (2013) Biochar in growing media: A sustainability and feasibility assessment

589 Steiner C, Harttung T (2014) Biochar as a growing media additive and peat substitute. *Solid Earth* 5:995–999.
590 <https://doi.org/10.5194/se-5-995-2014>

591 Tian Y, Sun X, Li S, et al (2012) Biochar made from green waste as peat substitute in growth media for *Calathea*
592 *rotundifolia* cv . *Fasciata*. *Sci Hortic (Amsterdam)* 143:15–18. <https://doi.org/10.1016/j.scienta.2012.05.018>

593 Torbaghan ME (2012) Effect of salt stress on germination and some growth parameters of marigold (*Calendula*
594 *officinalis* L.). *Plant Sci J* 1:7–19

595 van der Wal A, de Boer W (2017) Dinner in the dark: Illuminating drivers of soil organic matter decomposition.
596 *Soil Biol Biochem* 105:45–48. <https://doi.org/10.1016/j.soilbio.2016.11.006>

597 Vassilev S V., Baxter D, Andersen LK, Vassileva CG (2010) An overview of the chemical composition of
598 biomass. *Fuel* 89:913–933. <https://doi.org/10.1016/J.FUEL.2009.10.022>

599 Vaughn SF, Kenar JA, Thompson AR, Peterson SC (2013) Comparison of biochars derived from wood pellets
600 and pelletized wheat straw as replacements for peat in potting substrates. *Ind Crop Prod* 51:437–443.
601 <https://doi.org/10.1016/j.indcrop.2013.10.010>

602 Wallach R (2008) Physical characteristics of soilless media. In: *Soilless Culture: Theory and Practice*, 1st edn.
603 Elsevier Ltd., pp 41–116

604 Webber CL, White PM, Gu M, et al (2018a) Sugarcane and Pine Biochar as Amendments for Greenhouse
605 Growing Media for the Production of Bean (*Phaseolus vulgaris* L.) Seedlings. *J Agric Sci* 10:58.
606 <https://doi.org/10.5539/jas.v10n4p58>

607 Webber CL, White PM, Spaunhorst DJ, et al (2018b) Sugarcane Biochar as an Amendment for Greenhouse
608 Growing Media for the Production of Cucurbit Seedlings. *J Agric Sci* 10:104.
609 <https://doi.org/10.5539/jas.v10n2p104>

610 Weber K, Quicker P (2018) Properties of biochar. *Fuel* 217:240–261. <https://doi.org/10.1016/j.fuel.2017.12.054>

611 Wu P, Wang Z, Wang H, et al (2020) Visualizing the emerging trends of biochar research and applications in

612 2019: a scientometric analysis and review. *Biochar* 2:135–150. [https://doi.org/10.1007/s42773-020-00055-](https://doi.org/10.1007/s42773-020-00055-1)

613 1

614

ACCEPTED DRAFT

ACCEPTED DRAFT