DIFFUSION OF CALCIUM CHLORIDE IN A MODIFIED BENTONITE: IMPACT ON OSMOTIC EFFICIENCY AND HYDRAULIC CONDUCTIVITY

FRANCESCO MAZZIERI^{1,*}, GEMMINA DI EMIDIO², AND PETER O. VAN IMPE²

¹ Department of FIMET, Università Politecnica delle Marche, Via Brecce Bianche 60131 Ancona, Italy

² Laboratory of Geotechnics, Ghent University, TechnologiePark, 905, Zwijnaarde, Belgium

Abstract—Chemically modified bentonites are being developed with the aim of preserving low hydraulic conductivity in the presence of potentially aggressive permeants in pollutant-containment applications. ‘Multiswellable’ bentonite (MSB) has been obtained by treating standard sodium bentonite with propylene carbonate. Research on the engineering properties of MSB has focused mainly on permeability and chemical compatibility. Solute diffusion and membrane behavior in MSB have not yet been investigated. A combined chemico-osmotic/diffusion test was performed on a MSB specimen using a 5 mM CaCl₂ solution. Permeability with distilled water and with the 5 mM CaCl₂ solution was measured prior to and after the chemico-osmotic/diffusion tests. The material exhibited time-dependent membrane behavior with a peak osmotic efficiency value (ω) of 0.172 that gradually shifted to zero upon breakthrough of calcium ions. Effective diffusion coefficients of calcium and chloride ions were in the range commonly described for untreated bentonite at similar porosities. After the chemico-osmotic/diffusion stage and permeation with 5 mM CaCl₂, the hydraulic conductivity of MSB increased from 1.1×10^{-11} m/s to 7.0×10^{-11} m/s. The MSB was apparently converted into a calcium-exchanged bentonite at the end of the test. Prehydration and subsequent permeation might have contributed to elution of the organic additive from the clay. Further investigation is recommended to clarify the effect of prehydration on the hydraulic performance of MSB in the presence of potentially aggressive permeants.

Key Words—Chemico-osmotic Efficiency, Contaminant-resistant, Diffusion, Hydraulic Conductivity, Membrane, ‘Multiswellable’ Bentonite, Propylene Carbonate, Swelling.

INTRODUCTION

Bentonite has been used widely in engineered barriers for pollutant containment (e.g. soil-bentonite mixtures, cement-bentonite mixtures). Geosynthetic Clay Liners (GCLs) consisting of a thin layer of bentonite sandwiched between two geotextiles or glued to a geomembrane are increasingly used as hydraulic barriers in landfill covers and liners. The GCLs that do not include a geomembrane have hydraulic conductivity on the order of 10^{-11} m/s when permeated with deionized water or dilute aqueous solutions, owing to the low permeability properties of Na-montmorillonite, the main component of common bentonites (Bouazza, 2002). Unfortunately, the hydraulic conductivity of GCLs can be increased drastically by inorganic permeants that are aggressive to Na-montmorillonite, e.g. solutions with high concentrations and/or containing predominantly multivalent cations (Jo *et al.*, 2004).

Several types of contaminant-resistant bentonites have been developed with the aim of preserving low hydraulic conductivity in the presence of potentially aggressive permeants (Onikata *et al.*, 1996; Lo *et al.*, 1997; Ashmawy *et al.*, 2002). This paper presents test

results for MultiSwellable Bentonite (MSB), a chemically modified bentonite (Onikata *et al.*, 1999). Previous research on the engineering properties of MSB has focused mainly on permeability and chemical compatibility (Katsumi *et al.*, 2001; Mazzieri and Pasqualini, 2006; Katsumi *et al.*, 2008). In low-permeability barriers, diffusion may become the dominant pollutant-transport mechanism (Shackelford and Daniel, 1991). To the authors’ knowledge, solute diffusion in MSB has not yet been investigated. A combined chemico-osmotic/diffusion test was, therefore, performed on MSB using a 5 mM CaCl₂ solution. The primary purpose was to gather information on the diffusion of solutes in MSB. Secondly, the chemico-osmotic coefficient, ω , of MSB in the presence of the electrolyte solution was measured during the diffusion test. The purpose was to evaluate the ability of MSB to sustain membrane behavior and to compare the results with literature data on untreated bentonite. Finally, the impact of diffusion and subsequent permeation with 5 mM CaCl₂ on the hydraulic conductivity of MSB was evaluated.

PERMEABILITY AND MEMBRANE BEHAVIOR OF BENTONITES

The efficiency of bentonite as a component of hydraulic barriers is attributed to the large swelling capacity and low permeability of Na-montmorillonite. Swelling of montmorillonite from a dry state occurs in

* E-mail address of corresponding author:

f.mazzieri@univpm.it

DOI: 10.1346/CCMN.2010.0580306

two phases: the limited crystalline and the extensive crystalline (Quirk and Marčelja, 1997) or osmotic (Onikata *et al.*, 1999; Jo *et al.*, 2004) phases. In the former phase, water is absorbed as a result of the hydration of interlayer cations and solid surfaces until several monolayers of water molecules are bound in the interlayer. The latter phase consists of the macroscopic expansion of the clay volume as a result of further water adsorption in the interlayer space.

The extensive crystalline swelling is attributed to the interaction of diffuse double layers of contiguous clay surfaces, and the repulsive pressure acting between them can be modeled as the osmotic pressure difference between the center of the interlayer space and the bulk fluid (*e.g.* Bolt, 1956). Other authors have discounted the influence of double-layer interactions and attributed the extensive crystalline swelling to the structural perturbation of the interfacial water under the influence of the clays surface (*e.g.* Viani *et al.*, 1983).

For Na-montmorillonite, the osmotic phase of swelling is identified with d_{001} spacings reaching values >1.9 nm and it occurs if the hydrating liquid is pure water or a dilute solution, whereas it is prevented by electrolyte concentrations of >0.3 M NaCl (Norrish and Quirk, 1954). If multivalent cations (*e.g.* Ca^{2+} , Mg^{2+} , Al^{3+}) predominantly occupy the exchange complex, swelling is limited to the crystalline phase ($d_{001} \leq 1.9$ nm) even if the hydrating solution is pure water. In montmorillonites that undergo both crystalline and extensive swelling, a large number of water molecules is bound (hydraulically immobile). As a result, the fraction of the pore space occupied by bulk water that is free to flow is relatively small and the flow paths are tortuous and elongated. The clay has a dispersed structure in which clay particles are partly present as separated platelets and the hydraulic conductivity to water is typically very low (Mesri and Olson, 1971; Mitchell, 1993; Jo *et al.*, 2001, 2004).

Na-montmorillonite-rich clayey soils (*e.g.* bentonites) have been shown to behave as membranes, *i.e.* restrict the transport of solutes while a flow of water (chemical osmosis) is induced in the direction opposite to that of the chemical gradient (*e.g.* Katchalsky and Curran, 1965). The extent to which clays behave as semipermeable membranes has traditionally been quantified in terms of the osmotic efficiency coefficient ω (Mitchell, 1993). The membrane behavior of bentonite is being regarded with great interest in view of the beneficial impact on containment capability, since a barrier exhibiting chemical osmosis will generally perform better in terms of solute containment than a barrier where chemical osmosis is absent (Kejzer *et al.*, 1999; Malusis and Shackelford, 2002).

In the case of charged solutes, membrane behavior is generally attributed to electrostatic repulsion of the ions by electric fields generated by the overlapping diffuse double layers of closely spaced clay particles (Fritz,

1986). The restriction of solute transport by clayey soils is usually partial, so that the soil behaves like a 'leaky' or semi-permeable membrane allowing some flux of solutes. Hence, the chemico-osmotic behavior may be altered by the invasion (*e.g.* by molecular diffusion) of the pore space by solutes that cause compression of double layers, *e.g.* multivalent ions and/or high electrolyte concentrations (Mazzieri *et al.*, 2003; Shackelford and Lee, 2003). The same factors usually increase the hydraulic conductivity of common bentonites.

The MSB is a modified bentonite obtained by treating standard sodium bentonite with propylene carbonate (PC below), an aprotic polar organic solvent. Onikata *et al.* (1999) showed that PC forms complexes with homoionic montmorillonite by intercalation, and that the PC-montmorillonite complexes exhibit osmotic swelling (basal spacing $d_{001} > 1.9$ nm) in electrolyte solutions up to 0.75 M NaCl, whereas untreated bentonite exhibits osmotic swelling for NaCl concentrations of <0.3 M. The activating effect of PC on osmotic swelling has been explained in terms of solvent electron donor and acceptor properties (Onikata *et al.*, 2000). Treatment with PC not only improves the swelling properties but also the hydraulic conductivity of MSB. For example, permeability tests revealed that MSB had a hydraulic conductivity of 2.0×10^{-11} with 1 M NaCl whereas untreated bentonite had a hydraulic conductivity of 2.3×10^{-10} m/s (Katsumi *et al.*, 2008). Verifying whether modified bentonites such as MSB can sustain any membrane behavior is of great interest for containment applications (Shackelford, 2005).

MATERIALS AND METHODS

Materials

The MSB used in this study consisted of 80% Na-bentonite (NB hereafter) and 20% PC on a dry weight basis (*i.e.* the PC to NB weight ratio = 0.25). The MSB and NB were supplied to the authors by the producer (Hojun Kogyo Corp., Annaka, Gunma, Japan). The main physical and chemical properties of the clays were derived partly from the product information sheets and partly by standard soil-analysis procedures (see the Results section below).

Powder X-ray diffraction (XRD) analyses were performed on air-dried samples of MSB and NB using a Philips diffractometer (PW1730 X-ray generator, PW 1050/70 goniometer and $\text{CuK}\alpha$ radiation). No pretreatment of the clays was performed as the main purpose of the XRD analysis was to compare diffraction patterns and to observe the differences induced by the organic additive.

The liquids used in the study were distilled water (hereafter DW) and a 5 mM solution of CaCl_2 . The type and concentration of the solution were selected in order to allow comparison with results of a similar test on untreated Na-bentonite (Shackelford and Lee, 2003).

Distilled water ($\text{pH} = 5.8$, Electrical Conductivity, EC , = 1.7 mS/m) was produced using a water-distilling apparatus DZ 8103, Schott. The 5 mM CaCl_2 solution ($\text{pH} = 5.7$, $EC = 113 \text{ mS/m}$) was prepared by dissolving analytical-grade $\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$ (>99.9% Merck, Belgium) in DW.

Free swell tests

Free swell tests (ASTM D5890) were performed to examine the swelling behavior of MSB in the testing liquids (DW and 5 mM CaCl_2). Two grams of oven-dried clay were dusted carefully into a graduated cylinder containing the solution and the volume occupied by the clay ('free swell') was recorded after 24 h. Preliminary tests had shown some differences in the free swell results performed on air-dried or oven-dried MSB samples. In particular, the free swell was found to decrease significantly for oven-dried MSB compared to air-dried MSB. Heating at 105°C probably evaporated some of the weakly bound PC (Onikata *et al.*, 1999). Hence, MSB specimens to be used for further testing were not oven-dried. In order to estimate the gravimetric water content, separate portions of MSB were oven-dried at 105°C for 24 h. Although some of the recorded mass loss after oven drying might have been caused by evaporation of PC, no correction was adopted and the recorded mass loss was attributed entirely to water.

Chemico-osmotic/diffusion test

The combined chemico-osmotic/diffusion test was carried out by means of the testing apparatus described by Mazzieri *et al.* (2003), consisting essentially of the test cell and the pumping system (Figure 1). The cell

consisted of a lower mold and a pressure chamber separated by a rigid piston. The clay specimen was housed in the lower mold and confined between two porous plates. Swelling of the clay during the test was prevented by blocking the top piston.

The MSB specimen was prepared with a view to simulating thin bentonitic barriers like Geosynthetic Clay Liners. A thin layer of dry MSB was spread into the lower mold of the testing cell. The amount of bentonite used ($0.45 \text{ g dry solids/cm}^2$) was similar to that of commercial GCLs. The mold was subsequently inundated with DW and the specimen was allowed to swell unconfined to a height of $\sim 10 \text{ mm}$. The swollen MSB was then consolidated to the desired height of 7.4 mm (corresponding to a porosity of 0.717) by pressurizing the chamber above the top piston. The specimen was then permeated with DW to remove soluble salts, improve saturation, and measure the reference hydraulic conductivity.

After permeation, the chemico-osmotic/diffusion stage of the experiment commenced. A chemical gradient was induced across the specimens by circulating solutions of different concentrations at the specimen boundaries (*i.e.* the porous plates). The solutions were pumped at the same volumetric rate, q ($4.2 \times 10^{-7} \text{ L s}^{-1}$ in the present experiment). At the top boundary, the solution was infused at concentration $C_{t,i}$ ($= 5 \text{ mM CaCl}_2$) and withdrawn at concentration $C_{t,o} < C_{t,i}$ as a result of the diffusion of solutes (Ca^{2+} and Cl^-) into the clay. At the base boundary, the solution was infused at concentration $C_{b,i}$ (DW in this experiment, $C_{b,i} = 0$) and withdrawn at concentration $C_{b,o} > C_{b,i}$ as a result of solute diffusion from the clay. The outflow concentra-

Figure 1. Schematic view of the testing apparatus. Arrows indicate circulation flow directions (modified after Mazzieri *et al.*, 2003).

tions, $C_{t,o}$ and $C_{b,o}$, were monitored in order to evaluate the solute-mass flux across the specimen. Cation and anion concentrations in the outflow solutions were measured using a Varian SpectraAA 600 spectrophotometer.

As no water could leave or enter the clay, no fluid flow occurred across the clay; in the presence of osmotic behavior, a differential pressure arose that was measured by means of the differential pressure transducer (Figure 1). The osmotic efficiency coefficient ω [–] is defined as follows (Malusis *et al.* 2001):

$$\omega = \frac{\Delta P}{\Delta \pi} \quad (1)$$

where ΔP = the measured differential pressure [kPa] and $\Delta \pi$ = the theoretical osmotic pressure difference across an ideal semi-permeable membrane [kPa]. For the strong electrolyte (*i.e.* completely dissociated) solution used in the present study, the theoretical osmotic pressure difference can be expressed in accordance with the van't Hoff equation as:

$$\Delta \pi = vRT\Delta C \quad (2)$$

where v = the number of ions per salt molecule, R = the universal gas constant [$8.314 \text{ J mol}^{-1} \text{ K}^{-1}$], T = the absolute temperature [K], ΔC = the salt concentration difference [mol L^{-1}].

At the beginning of the experiment, DW was first circulated for 1 day at both ends of the specimen to establish a reference differential pressure and remove residual salts from the porous plates. The 5 mM CaCl_2 solution was then circulated at the top end of the specimen until the steady states of the differential pressure and the diffusive flux were reached. Finally, permeation with 5 mM CaCl_2 was carried out in order to assess the impact of the solution on the hydraulic conductivity of MSB.

Test interpretation

During chemico/osmotic-diffusion experiments, solute diffusion usually displays a transient phase, with variable $C_{t,o}$ and $C_{b,o}$, and a steady-state phase, with constant $C_{t,o}$ and $C_{b,o}$. To evaluate the solute-diffusion coefficient by the steady-state approach, the cumulative mass per unit area, Q_t [mol m^{-2}], of a given solute was calculated as (Malusis *et al.*, 2001):

$$Q_t = \frac{1}{A} \sum_{k=1}^N \Delta V_k (c_{b,o})_k \quad (3)$$

where Δm_k = the mass increment [mol] in the k^{th} sample collected over a given time interval Δt , ΔV_k = the outflow volume for the k^{th} sample [L], $(c_{b,o})_k$ = the outflow base solute concentration measured in the k^{th} sample, and N = the total number of samples collected. The Q_t vs. t plot usually presents a curved portion

(transient diffusion) and a linear portion (steady-state diffusion). The extrapolated intersection of the linear portion with the time axis is referred to as 'time-lag,' t_L , whereas the intersection of the curved transient portion with the linear portion corresponds to the steady-state diffusive flux and is denoted as t_{ss} . The slope of Q_t vs. t plot at steady state is related to the diffusive mass flux J by:

$$J = \frac{\Delta Q_t}{\Delta t} \quad (4)$$

At steady state, Fick's first law of diffusion in soils (Crank, 1975) gives:

$$J = nD \frac{(\bar{C}_t - \bar{C}_b)}{H} \quad (5)$$

where J = the steady-state diffusive mass flux [$\text{mol m}^{-2} \text{ s}^{-1}$], $\bar{C}_t$ = the average solute concentration in the top plate [mol L^{-1}], $\bar{C}_b$ = the average solute concentration in the base plate [mol L^{-1}], D = the bulk solute diffusion coefficient [$\text{m}^2 \text{ s}^{-1}$], H = the specimen thickness [m], and n = the total clay porosity [–]. The bulk diffusion coefficient, D [$\text{m}^2 \text{ s}^{-1}$], is defined as follows (Manassero and Dominijanni, 2003):

$$D = (1 - \omega)\tau D_0 \quad (6)$$

where τ = the geometric tortuosity factor (–) and D_0 = the solute free diffusion coefficient [$\text{m}^2 \text{ s}^{-1}$]. Assuming that sorption of the solute on the clay can be represented by a linear isotherm, t_L is related to the retardation factor R_d [–] as follows (Crank, 1975):

$$R_d = \frac{6Dt_L}{H^2} \quad (7)$$

Note that equation 7 derives from a closed-form solution to Fick's second law of diffusion in soils for a neutral solute undergoing linear sorption, for perfect flushing boundary conditions and an initial zero solute concentration across the clay. In the case of a binary electrolyte, the cation of which undergoes exchange by the clay, the rigorous transport model that accounts for linear sorption, the osmotic effect, and the constraint of electroneutrality consists of a coupled system of non-linear partial differential equations that must be solved numerically (Malusis and Shackelford, 2002). Application of equation 7 to the transient transport of individual ions of a binary electrolyte results in a 'lumped' retardation factor that includes solute restriction, sorption, and electrical interaction between ions (Van Impe *et al.*, 2005).

RESULTS AND DISCUSSION

Materials characterization

The untreated NB had a similar cation exchange capacity (CEC), cation occupancy, and free swell

Table 1. Physical and chemical properties of the MSB and NB bentonites.

Property	Source/method	Value	
Product name	Information sheet	Multigel® (MSB)	Superclay®(NB)
Principal mineral	Information sheet	Montmorillonite	Montmorillonite
Water content (%)	ASTM D4959	21	10
Specific gravity, G_s (—)	ASTM D 854	2.15	2.63
Liquid limit (%)	ASTM D4318	554	683
Clay pH	^a	7.0	9.0
Electrical conductivity (mS/m)	^a	18.8	15.3
Cation exchange capacity (meq/100 g)	—	52.6 ^b	72.3 ^c
Exchangeable cations(meq/100 g):			
Na ⁺		41.0 ^b	45.4 ^c
Ca ²⁺	—	16.9 ^b	19.1 ^c
Mg ²⁺		6.8 ^b	9.6 ^c
K ⁺		0.8 ^b	1.0 ^c
Soluble cations (meq/100 g):	^d		
Na ⁺		13.5	2.0
Ca ²⁺		1.7	0.4
Mg ²⁺		0.8	0.8
K ⁺		0.6	0.8
Free swelling (mL)	ASTM D5890	23	22

^a Measured on a 1:50 bentonite-water extract.

^b Based on the method of Sumner and Miller (1996).

^c Data from Mishra *et al.* (2006).

^d Based on the method after Rhoades (1996)

(Table 1) to bentonites used in commercial GCLs, particularly to those that have proven to behave as semi-permeable membranes (Malusis and Shackelford, 2001; Shackelford and Lee, 2003). NB was, therefore, assumed to exhibit chemico-osmotic behavior under suitable conditions (*i.e.* small salt concentrations, small thickness).

The specific gravity of MSB (2.15) as per ASTM D 854 was significantly smaller than that of untreated NB (2.63), which was consistent with the binding of PC molecules in the interlayer of montmorillonite (Kolstad *et al.*, 2004). The exchangeable cations of MSB,

previously washed with DW, were displaced with an ammonium acetate solution, following the procedure indicated by Sumner and Miller (1996). Sodium was the dominant cation, with a significant calcium content, analogous to NB. The sum of exchangeable cations exceeded the CEC, probably as a result of incomplete removal of soluble salts during washing with DW. Hence, the exchangeable cation concentrations may include a fraction of soluble cations.

The main feature of the XRD patterns (Figure 2) was the shift in the d_{001} basal spacing of the MSB ($d_{001} = 1.78$ nm) compared to NB ($d_{001} = 1.23$ nm), reflecting

Figure 2. XRD patterns of MSB bentonite and NB bentonite.

the presence of PC molecules coordinated with exchangeable cations in the interlayers.

Onikata *et al.* (1999) presented the basal spacings of air-dried homo-ionic montmorillonites mixed with various concentrations of PC. The basal spacing of homoionic Na, Ca, and Mg montmorillonites mixed with 25% PC was 1.9 nm, suggesting the formation of bi-layers of PC between the silicate layers, whereas the d_{001} spacing for K-montmorillonite was 1.4 nm with a mono-layer of PC molecules being formed. The d_{001} spacing of air-dried MSB observed in this study (1.78 nm) was intermediate between the values observed for bi- and mono-layers of PC molecules, probably as a result of mixed cation occupation and/or slightly different residual water contents after air-drying.

Free swell

In an attempt to simulate the sequence of exposure of the chemico-osmotic/diffusion test, the same MSB was used for the free swell tests in DW and in 5 mM CaCl_2 . After completion of the test in DW, the bentonite was recovered, air-dried, and reused for the test with 5 mM CaCl_2 . The free swell of MSB in DW was 23 mL whereas in 5 mM CaCl_2 the free swell was 50 mL. The base NB bentonite gave 22 mL in DW and 27 mL in 5 mM CaCl_2 . Onikata *et al.* (2000) attributed the swelling of MSB in electrolyte solutions to the formation of thick electrical double layers consisting of PC and water that coordinate with the interlayer cations between the silicate layers. The MSB swollen in 5 mM CaCl_2 formed large flocs that did not remold completely when settled, which may partly explain the large swell volume. Moreover, the supernatant was relatively clear whereas it was rather turbid with DW, reflecting the tendency of the clay particles to remain suspended. The same trend of increasing swell with 5 mM CaCl_2 compared to DW and the tendency to form flocs was also observed in NB, albeit to a much lesser extent.

Katsumi *et al.* (2008) reported results of free swell tests on MSB in DW and in CaCl_2 solutions for concentrations ranging from 0.1 M to 0.5 M. They found that the free swell of MSB in CaCl_2 solutions was always less than in DW, but they reported no data for concentrations of <0.1 M. Katsumi *et al.* (2008) also found that free swell results did not always correlate well with other properties of MSB. For example, they observed that the free swell of MSB increased from 28 mL in DW to 40 mL in 0.5 M NaCl, but the Liquid Limit decreased from 500% in DW to 320% in 0.5 M NaCl. The hydraulic conductivity remained substantially unaltered, varying from 1.0×10^{-11} m/s in DW to 1.3×10^{-11} m/s in 0.5 M NaCl. As a consequence, a considerable increase in the swelling power of MSB in a given liquid does not necessarily reflect a substantial improvement in terms of hydraulic conductivity.

Permeation with DW

Permeation with DW was continued until the Electrical Conductivity (EC) of the effluent solution (Figure 3) was significantly less than the EC of the 5 mM CaCl_2 solution (113 mS/m). The EC of the effluent was initially approximately double the EC of the 5 mM CaCl_2 solution. The final EC of effluent was 25 mS/m, less than one-fourth of the source solution. The hydraulic conductivity (k) of the specimen (Figure 3) was calculated from the measured effluent volume during permeation and the applied gradient in accordance with Darcy's Law. A relatively large hydraulic gradient (≈ 770) was used in order to shorten the flushing stage, which still lasted ~ 90 days. The calculated k of the MSB specimen with DW was relatively constant at $\approx 1.1 \times 10^{-11}$ m/s.

Chemico-osmotic efficiency

In the chemico-osmotic/diffusion stage of the test, the differential pressure across the MSB specimen was

Figure 3. Hydraulic conductivity of MSB specimen permeated with distilled water, and electrical conductivity of the effluent.

monitored with time (Figure 4). The hydraulic pressure and the osmotic pressure decreased with increasing vertical distance (positive x) from the top boundary of the specimen; hence $-\Delta P$ was plotted. During circulation of DW, a non-zero average differential pressure $(-\Delta P)_0 \approx 1.0$ kPa was measured, probably as a result of slightly different hydraulic conductivities of the porous plates (Malusis *et al.*, 2001) and/or different residual salt content.

Replacement of DW with the 5 mM CaCl_2 solution caused an immediate increase in the differential pressure to a peak value $(-\Delta P)_{\max} = 7.3$ kPa. The peak value occurred within ~ 16 h of the circulation with the source solution. The differential pressure dropped gradually thereafter to values fluctuating around $(-\Delta P)_0$. Considering the scatter of the measurements, evaluating the steady state of the differential pressure exactly was difficult. Somewhat arbitrarily the steady state of $-\Delta P$ was assumed to have been achieved when the $-\Delta P$ vs. time curve first crossed the line representing $(-\Delta P)_0$, *i.e.* after ~ 22 days of circulation with the solution. The osmotic efficiency was calculated using equation 1. The steady-state osmotic efficiency was $\omega_{ss} = 0$. The peak osmotic efficiency, $\omega_{\max}$, was calculated from equation 1 using $\Delta P = -6.3$ kPa and $\Delta\pi = -36.6$ kPa, which is the maximum theoretical osmotic pressure difference calculated from the van't Hoff equation (equation 2) for $\Delta C = -5$ mM, $v = 3$, and $T = 293.15$ K. The maximum osmotic efficiency coefficient was $\omega_{\max} = 0.172$. Therefore, the MSB specimen initially exhibited membrane behavior ($\omega > 0$), which was gradually destroyed ($\omega = 0$) during the test.

Solute diffusion

The impact of solute diffusion was assessed by analysis of the Ca^{2+} and Cl^- concentrations in the outflow solutions over time (Figure 5). Concentrations

were expressed in meq/L in order to visualize the balance between positive and negative charges. The breakthrough of Cl^- in the base outflow occurred much earlier than for Ca^{2+} . The transport of Ca^{2+} was, therefore, retarded compared with Cl^- . Adsorption of Ca^{2+} occurred as a result of exchange with Na^+ , the major exchangeable cation of MSB (Table 1), as confirmed by measurement of Na^+ concentrations in the outflow solutions. The dashed lines (Figure 5) represent the sum of Na^+ and Ca^{2+} equivalents in the outflow solutions. The lines tend to approach those representing Cl^- , in accordance with the requirement for electroneutrality of solutions.

During the transient phase of the test, both Na^+ and Ca^{2+} ions diffused downwards together with Cl^- in order to satisfy the electrical balance. Observe that exchanged Na^+ also diffused upwards into the top outflow solution. Release of Na^+ into the clay pore fluid as a result of exchange with Ca^{2+} created a local Na^+ concentration gradient between the clay close to the top boundary and the fresh 5 mM CaCl_2 solution (which was free from Na^+) so that counter-diffusion of Na^+ occurred in the direction opposite to that of the main chemical gradient (Jugnicket *et al.*, 2004). Despite a certain scatter in the concentration measurements, the steady state for Ca^{2+} diffusion was apparently achieved.

To evaluate the solute-transport parameters, D (bulk diffusion coefficient) and R_d (retardation factor), the trends in Q_t vs. time were analyzed by the time-lag method (Figure 6a,b). The results of the analysis (Table 2) were obtained for a total porosity $n = 0.717$ and specimen height $H = 7.4$ mm.

The steady-state bulk-diffusion coefficients of Cl^- and Ca^{2+} were very close, in accordance with the electroneutrality constraint. With $\omega = 0$ at steady state, the bulk diffusion coefficients defined by equation 6 coincide with the product of the geometric tortuosity

Figure 4. Differential pressure vs. time recorded during the chemico-osmotic stage of the experiment (redrawn after Mazzieri *et al.*, 2005).

Figure 5. Solute concentrations in the outflow solutions at the top and bottom boundaries of the MSB specimen during the chemico-osmotic/diffusion stage of the experiment (redrawn after Mazzieri *et al.*, 2005).

Figure 6. Trends in cumulative mass per unit area Q_t vs. t for Cl^- (a) and Ca^{2+} (b).

Table 2. Solute transport parameters.

Solute	Time-lag, t_L^a (days)	Steady-state, t_{ss}^a (days)	$D \cdot 10^{10}$ (m^2/s)	R_d (—)
Cl^-	2.8	11.5	1.79	4.6
Ca^{2+}	13.7	30.0	1.60	17.5

^a1 day of circulation with DW has been deducted.

factor and the free diffusion coefficient, often referred to as the effective diffusion coefficient (D^*) in the geotechnical literature (*e.g.* Shackelford and Daniel, 2001; Malusis *et al.*, 2001). The values of bulk-diffusion coefficients compare well with published data regarding the effective diffusion coefficients of Ca^{2+} and Cl^- in untreated bentonite at similar porosities (Shackelford and Lee, 2003).

The steady-state diffusion of Cl^- based on time-lag analysis occurred much earlier (11.5 days) than for Ca^{2+} (30 days). Based on the calculated R_d values, both Cl^- and Ca^{2+} were retarded ($R_d > 1$). Firstly, the calculated R_d value may depend upon the adopted interpretation of the transient phase of the test. The time-lag method fails to take into account electrostatic interactions between ions and assumes that the boundary concentrations are maintained constant throughout the test, whereas the boundary concentrations changed during the test as a result of diffusion (Figure 5).

Release of Na^+ cations during diffusion of Ca^{2+} suggested that cation exchange onto the clay surface was the main retarding process for Ca^{2+} . The chemico-osmotic effect and the electrostatic interaction among the diffusing ions also had a role in the transient transport of Ca^{2+} . Cl^- is usually considered a con-

servative tracer in clay diffusion studies since it tends to be repelled from negatively charged surfaces. Theoretically, a conservative tracer should have $R_d = 1$. Besides solute restriction ($\omega > 0$), the retardation of Cl^- could be partly explained by the counter-diffusion of Na^+ into the top solution, which may have delayed the downward diffusion of Cl^- due to the electrical interaction.

Permeation with calcium chloride

After completion of the chemico-osmotic stage of the test, the MSB specimen was permeated with the 5 mM CaCl_2 solution from the top downwards, *i.e.* in the same direction as the chemical gradient imposed. The hydraulic conductivity of MSB with the electrolyte solution and the *EC* of the effluent were monitored (Figure 7). For the sake of comparison, the hydraulic conductivity and *EC* during permeation with DW and the *EC* of the outflow solution during the chemico-osmotic/diffusion stage of the test are also displayed. While still very small, the hydraulic conductivity with 5 mM CaCl_2 showed an increase to $\sim 7.0 \times 10^{-11}$ m/s compared to 1.1×10^{-11} m/s obtained with DW. Thereafter, the k value remained approximately constant, with the *EC* of the effluent gradually approaching the *EC* value of the influent solution, suggesting complete replacement of the pore fluid. The piston remained blocked during permeation, so that no additional swelling could occur. In principle, shrinkage of the specimen was not impeded and, therefore, the clay might have detached from the cell walls resulting in sidewall leakage. The evidence at the end of the test seemed to rule out this possibility, however.

Firstly, extracting the clay from the cell was rather difficult, suggesting that a certain pressure was exerted

Figure 7. Hydraulic conductivity of MSB vs. t during permeation with DW and with 5 mM CaCl_2 solution and *EC* of the effluent solutions.

against the walls. Some bentonite solids even remained attached to the cell. Secondly, sidewall leakage would probably have resulted in much greater hydraulic conductivity. In brief, the increase in hydraulic conductivity was related to physicochemical changes induced in the MSB bentonite by the salt solution.

DISCUSSION

The results obtained in this study qualitatively resemble previous findings by Shackelford and Lee (2003) on untreated bentonite (GCL). Those authors observed a variable osmotic efficiency exhibiting a peak value, followed by a gradual decrease to zero. They concluded that the time required to destroy the membrane behavior correlated almost exactly with the time required to reach steady-state diffusive transport of Ca^{2+} ions through the GCL specimen, and attributed the destruction of chemico-osmotic behavior to the compression of diffuse double layers, caused by increasing concentrations of divalent Ca^{2+} in the pore fluid. The results are also in accordance with Bresler (1973) who showed theoretically that the osmotic efficiency decreases with increasing concentration and increasing cation valence. As mentioned earlier, the estimated time required for the destruction of chemico-osmotic behavior of MSB in this study was 22 days, whereas the steady-state diffusion of Ca^{2+} was reached after 30 days. The scatter in the measurement of the differential pressure may, however, have precluded the exact assessment of the steady state. Although the correlation with steady-state diffusion was less evident than in the study carried out by Shackelford and Lee (2003), the diffusion of Ca^{2+} cations and the consequent change in clay fabric was probably the main factor responsible for the destruction of chemico-osmotic behavior of MSB.

Test results can be interpreted considering that montmorillonites are organized in quasicrystals (Aylmore and Quirk, 1971), each consisting of several individual layers stacked together. Laird (2006) pointed out that crystalline swelling is a process that occurs within quasicrystals, whereas double-layer swelling occurs between quasicrystals. At the clay/water ratio achieved by the clay during the test, quasicrystals will likely not exfoliate completely. The structure of the hydrated bentonite will consist of a mixture of particle aggregates and individual particles, where double layers extend into voids between quasicrystals and around delaminated individual particles, which reorganize to form soft gels in the open voids (Pusch and Weston, 2003; Guyonnet *et al.* 2005). In such a structure, most of the water is bound and the hydraulic conductivity to water is typically very low (Mesri and Olson, 1971; Mitchell, 1993; Jo *et al.*, 2001, 2004).

The restriction of ions is greatest when the double layers of adjacent particles overlap in the pore space, leaving little or no free solution for ion transport

(Shackelford and Malusis, 2002). A variation of double-layer thickness and related electrical potentials in the pore space will, therefore, generally influence both the pore space available to solvent flow (*i.e.* the hydraulic conductivity) and the fraction of pore space available to ions and solvent flow (*i.e.* the osmotic efficiency). At constant total porosity, compression of the double layers due to the exchange of Ca^{2+} for Na^{+} results in an increase in the fraction of pore space available to water transport and a reduction of the pore space restricted to ions. Hence, the increase in permeability is consistent with the observed decrease in chemico-osmotic efficiency (Wintworth and Fritz, 1994; Malusis and Shackelford, 2001).

The results suggested that a modification of the initial properties conferred by PC occurred during the test. According to Onikata *et al.* (1999), PC is bound to the bentonite by coordination with the adsorbed cations in the interlayer of montmorillonite. As the exchange of Ca^{2+} for Na^{+} cations was demonstrated, the question arises as to whether the exchangeable Na^{+} was removed together with the coordinated PC clouds. Direct assessment of the release of either PC in the effluent solutions or the presence of PC in the MSB at the end of the test was not possible. Comparison of the dry mass of the specimen before and after the test revealed a mass loss of ~2.00 g, which can be partly attributed to the solids which remained attached to the cell and to the removal of PC during permeation and/or oven-drying. Considering the initial, nominal content of PC in MSB (20%), a calculation showed that 3.56 g of PC was initially bound in the specimen. Even if the mass loss of 2.00 g was entirely attributed to PC, 1.56 g of PC would remain bound to the clay.

Free swell tests were performed on the MSB retrieved from the specimen: the free swell was 11 mL in DW and 10 mL in 5 mM CaCl_2 . These values were significantly different from the results obtained on unused MSB (23 mL in DW and 50 mL in 5 mM CaCl_2) and were close to values commonly obtained with Ca-bentonites (Egloffstein, 2001). In short, at the end of the test, the MSB appeared to have converted into a Ca-exchanged bentonite partially or totally deprived of PC and of the swelling properties initially conferred by PC. Conversion into a Ca-bentonite probably occurred during the diffusion stage and partly during permeation with 5 mM CaCl_2 .

Katsumi *et al.* (2008) performed permeability tests on granular MSB with deionized water with and CaCl_2 solutions ranging from 0.1 M to 0.5 M. Permeation was carried out at effective stress of 20–30 kPa and for test duration of up to 2 years. For deionized water, $k = 1.5 \times 10^{-11}$ m/s was found, very close to the value $k = 1.0 \times 10^{-11}$ m/s obtained in the present study using DW. Katsumi *et al.* (2006) obtained $k = 6.2 \times 10^{-11}$ m/s with 0.1 M CaCl_2 , however, and $k = 6.5 \times 10^{-11}$ m/s with 0.5 M CaCl_2 as opposed to $k = 7 \times 10^{-11}$ m/s with

5mM CaCl_2 found in the present study. In short, they found a similar permeability of MSB with significantly greater calcium concentrations. Several possible reasons for the difference exist. Firstly, a dry mass of solids per unit area of 0.80 g/cm^2 was used by those authors to prepare the specimens vs. 0.45 g/cm^2 used in the present study. Secondly, the use of flexible-wall permeameters as opposed to the rigid-wall testing cell and fixed specimen height used in this study may be significant. Finally, in the present study, the MSB was prehydrated and permeated with DW prior to exposure and permeation with the CaCl_2 solution, whereas the MSB was permeated directly with the solutions in the Katsumi *et al.* (2008) study. In accordance with the molecular model of PC-montmorillonite complexes suggested by Onikata *et al.* (1999), swelling of MSB occurs as water molecules are attracted inside the PC clouds that surround the interlayer cations. During the initial hydration phase, the MSB specimen was allowed to swell freely with DW. Several molecular layers of water were attracted around the interlayer cations, which could have weakened the intermolecular bond between PC and interlayer cations, so that the PC could eventually have been released. Permeation with DW to wash out soluble salts may also have facilitated elution of PC from the clay. Mazzeri and Pasqualini (2006) observed that MSB permeated directly with natural seawater had a hydraulic conductivity of $5 \times 10^{-11} \text{ m/s}$, whereas MSB prehydrated with DW and then permeated with natural seawater had a hydraulic conductivity of $1.5 \times 10^{-10} \text{ m/s}$; which contrasts with the behavior of both untreated (Shackelford *et al.*, 2000) and polymer-treated bentonites (Ashmawy *et al.*, 2002), for which prehydration usually produces lower permeability than direct contact with a given solution. Further investigations are necessary to clarify the effect of prehydration on the hydraulic performance of MSB in the presence of a potentially aggressive solution.

CONCLUSIONS

A combined chemico/osmotic diffusion test was carried out in order to investigate solute diffusion and to evaluate the potential for membrane behavior of a chemically modified bentonite (MSB), obtained by treating base sodium bentonite with propylene carbonate. The chemico-osmotic/diffusion stage of the test was performed using a 5 mM CaCl_2 solution. The diffusion stage was preceded by permeation with distilled water and followed by permeation with the 5 mM CaCl_2 solution.

The steady-state solute-diffusion coefficients in MSB were $1.60 \times 10^{-10} \text{ m}^2/\text{s}$ for Ca^{2+} and $1.79 \times 10^{-10} \text{ m}^2/\text{s}$ for Cl^- , respectively. The values were very close, in accordance with the requirement for electroneutrality, and compared well with values commonly described for untreated bentonites under similar conditions. The MSB

exhibited a time-dependent membrane behavior, with a peak osmotic efficiency ω of 0.172 followed by a gradual reduction to $\omega = 0$. The reduction of osmotic efficiency was associated with the breakthrough of Ca^{2+} cations through the specimen and the release of Na^+ cations. The hydraulic conductivity increased from $1.1 \times 10^{-11} \text{ m/s}$ in DW to $7.0 \times 10^{-11} \text{ m/s}$ in 5 mM CaCl_2 . The increase in hydraulic conductivity was also attributed to the invasion of pore space by Ca^{2+} cations.

Although direct evidence of the concomitant release of the organic additive during the test was not provided in this study, the final properties of the MSB (free swell, hydraulic conductivity) were consistent with those of an untreated and calcium-exchanged bentonite. Prehydration and subsequent permeation water might have contributed to elution of the organic additive from the clay. More research is warranted to extend the results of this study to different solutes, different porosities, and to different testing methods. In particular, further investigations are necessary to clarify the effect of prehydration on the hydraulic performance of MSB in the presence of potentially aggressive permeants.

LIST OF ABBREVIATIONS

GCL = geosynthetic clay liner
 MSB = multiswellable bentonite
 NB = base (untreated) bentonite
 PC = propylene carbonate
 CEC = cation exchange capacity
 DW = distilled water
 EC = electrical conductivity

ACKNOWLEDGMENTS

Financial support to the research program was provided by Ghent University through GOA grant 12.058.598. The tests described in this paper are part of the doctoral thesis of Mrs Gemmina di Emidio. The authors are grateful to Dr. M. Onikata of Hojun Kogyo Corp., Japan, for supplying the bentonite materials used in this study and for the useful discussions.

REFERENCES

- Ashmawy, A.K., El-Hajji, D., Sotelo, N., and Naim, M. (2002) Hydraulic performance of polymer-treated bentonite in inorganic landfill leachates. *Clays and Clay Minerals*, **50**, 546–553.
- Aylmore, L.A.G. and Quirk, J.P. (1971) Domains and quasi-crystalline regions in clay systems. *Soil Science Society of America Journal*, **35**, 652–654.
- Bolt, G.H. (1956) Physico-chemical analysis of the compressibility of pure clays. *Géotechnique*, **6**, 86–93.
- Bouazza, A. (2002) Geosynthetic Clay Liners. *Geotextiles and Geomembranes*, **20**, 3–17.
- Bresler, E. (1973) Anion exclusion and coupling effects in nonsteady transport through unsaturated soil: I. Theory. *Soil Science Society of America Journal*, **37**, 663–669.
- Crank, J. (1975) *The Mathematics of Diffusion* (2nd edition). Clarendon Press, Oxford, UK, 414 pp.
- Egloffstein, T.A. (2001) Natural bentonites: influence of the

- ion exchange and partial desiccation on permeability and self-healing capacity of bentonites used in GCLs. *Geotextiles and Geomembranes*, **19**, 427–444.
- Fritz, J. (1986) Ideality of clay membranes in osmotic processes: A review. *Clays and Clay Minerals*, **34**, 214–223.
- Guyonnet, D., Gaucher, E., Gaboriau, H., Pons, C.-H., Norotte, V., and Didier, G. (2005) Geosynthetic clay liner interaction with leachate: correlation between permeability, microstructure, and surface chemistry. *Journal of Geotechnical and Geoenvironmental Engineering*, **131**, 740–749.
- Jo, H.Y., Katsumi, T., Benson, C.H., and Edil, T.B. (2001) Hydraulic conductivity and swelling of non-prehydrated GCLs permeated with single species salt solutions. *Journal of Geotechnical and Geoenvironmental Engineering*, **127**, 557–567.
- Jo, H.Y., Katsumi, T., Benson, C.H., and Edil, T.B. (2004) Hydraulic conductivity and cation exchange in non-prehydrated and pre-hydrated bentonite permeated with weak inorganic solutions. *Clays and Clay Minerals*, **52**, 661–679.
- Jugnicket, C., Smith, D., and Fityus, S. (2004) Coupled multi-ion electrodiffusion analysis for clay soil. *Canadian Geotechnical Journal*, **41**, 287–298.
- Katchalsky A. and Curran, P.F. (1965) *Nonequilibrium Thermodynamics in Biophysics*. Harvard University Press, Cambridge, Massachusetts, USA, 248 pp..
- Katsumi, T., Onikata, M., Hasegawa, S., Lin, L., Kondo, M., and Kamon, M. (2001) Chemical compatibility of modified bentonite permeated with inorganic solutions. Pp. 419–424 in: *Geoenvironmental Engineering, Geoenvironmental Impact Management* (R.N. Yong and H.R. Thomas, editors). Thomas Telford, London.
- Katsumi, T., Ishimori, H., Onikata, M., and Fukagawa, R. (2008) Long-term barrier performance of modified bentonite materials against sodium and calcium permeant solutions. *Geotextiles and Geomembranes*, **26**, 14–30.
- Kijzer, Th., Kleingeld, P.J., and Loch, J.P.G. (1999) Chemical osmosis in compacted clayey material and the prediction of water transport. *Engineering Geology*, **53**, 151–159.
- Kolstad, D.C., Benson, C.H., Edil, T.B., and Jo, H.Y. (2004) Hydraulic conductivity of a dense prehydrated GCL permeated with aggressive inorganic solutions. *Geosynthetics International*, **11**, 233–241.
- Laird, D.A. (2006) Influence of layer charge on swelling of smectites. *Applied clay science*, **34**, 74–87.
- Lo, I.M.C., Mak, R.K.M., and Lee, S.C.H. (1997) Modified clays for waste containment and pollutant attenuation. *Journal of Environmental Engineering*, **123**, 25–32.
- Malusis M. and Shackelford, C.D. (2001) Chemo-osmotic efficiency of a geosynthetic clay liner. *Journal of Geotechnical and Geoenvironmental Engineering*, **128**, 97–106.
- Malusis, M. and Shackelford, C.D. (2002) Theory for reactive solute transport through clay membrane barriers. *Journal of Contaminant Hydrology*, **59**, 291–316.
- Malusis, M.A., Shackelford, C.D. and Olsen, H.W. (2001) A laboratory apparatus to measure the chemico-osmotic efficiency for clay soils. *Geotechnical Testing Journal*, **24**, 229–242.
- Manassero, M. and Dominijanni, A. (2003) Modelling the osmosis effect on solute migration through porous media. *Géotechnique*, **53**, 481–492.
- Mazzieri, F. and Pasqualini, E. (2006) Evaluating the permeability of an organically modified bentonite to natural seawater. Pp. 749–756 in: *Proceedings of the IVth International Conference on Environmental Geotechnics, Cardiff* (H.R. Thomas editor). Thomas Telford,
- Mazzieri, F., Van Impe, P.O., Van Impe, W.F., and Constales, D. (2003) Measurement of chemico-osmotic parameters of clayey soils. *Proceedings XIIIth European Conference ISSMGE, Prague* (I. Vanicek et al. editors) Czech Geotechnical Society CICE, pp. 433–438.
- Mesri, G. and Olson, R.E. (1971) Mechanisms controlling the permeability of clays. *Clays and Clay Minerals*, **19**, 151–158.
- Mitchell, J.K. (1993) *Fundamentals of Soil Behaviour* (2nd edition). Wiley, NY, 437 pp.
- Mishra, A.K., Ohtsubo, M., Li, L., and Higashi, T. (2006) Effect of salt concentrations on the hydraulic conductivity of the mixtures of basalt soil and various bentonites. *Journal of Agricultural Faculty, Kyushu University, Japan*, **51**, 37–43.
- Norrish, K. and Quirk, J.P. (1954) Crystalline swelling of montmorillonite. Use of electrolytes to control swelling. *Nature*, **173**, 255–256.
- Onikata M., Kondo M., and Kamon, M. (1996) Development and characterization of a multiswellable bentonite. *Proceedings of the 2nd International Conference on Environmental Geotechnics* (M. Kamon, editor). Balkema, Rotterdam, pp. 587–590.
- Onikata, M., Kondo, M., Hayashi, N., and Yamanaka, S. (1999) Complex formation of cation-exchanged montmorillonites with propylene carbonate: Osmotic swelling in aqueous electrolyte solutions. *Clays and Clay Minerals*, **47**, 672–677.
- Onikata M., Fujita K., Kondo M., and Yamanaka, S. (2000) Complex formation of homoionic montmorillonite with propylene carbonate and osmotic swelling in aqueous electrolyte solutions. *Molecular Crystals and Liquid Crystals*, **341**, 345–350.
- Pusch, R. and Weston, R. (2003) Microstructural stability controls the hydraulic conductivity of smectitic buffer clay. *Applied Clay Science*, **23**, 35–41.
- Quirk, J.P. and Marčelja, S. (1997) Application of double-layers theories to extensive crystalline swelling of Li-montmorillonite. *Langmuir*, **13**, 6241–6248.
- Rhoades, J.D. (1996) Salinity: electrical conductivity and total dissolved solids. Pp. 417–435 in: *Method of Soil Analysis Part 3* (D.L. Sparks, editor). SSSA, Madison, Wisconsin, USA.
- Shackelford, C.D. (2005) Environmental issues in geoenvironmental engineering. *Proceedings XVIth International Conference ISSMGE, Osaka*. Millpress, The Netherlands, pp. 95–122.
- Shackelford, C.D. and Daniel, D.E. (1991) Diffusion in saturated soils, I: Background. *Journal of Geotechnical Engineering*, **117**, 467–484.
- Shackelford, C.D. and Lee, J. (2003) The destructive role of diffusion on clay membrane behavior. *Clays and Clay Minerals*, **51**, 186–196.
- Shackelford, C.D. and Malusis, M.A. (2002) Clay membrane behavior and coupled solute diffusion. Pp. 289–297 in: *Chemo-Mechanical Coupling in Clays; from a Nano-Scale to Engineering Applications* (C. Di Maio et al., editors). Swets & Zeitlinger Publishers, The Netherlands.
- Shackelford, C.D., Benson, C.H., Katsumi, T., Edil, T.B., and Lin, L. (2000) Evaluating the hydraulic conductivity of GCLs permeated with nonstandard liquids. *Geotextiles and Geomembranes*, **18**, 133–161.
- Sumner, M.E. and Miller, W.P. (1996) Cation exchange capacity and exchange coefficients. Pp. 1201–1229 in: *Methods of Soil Analysis Part 3* (D.L. Sparks, editor). Soil Science Society of America, Madison, Wisconsin, USA.
- Van Impe, P.O., Van Impe, W.F., and Mazzieri, F. (2005) Impact of osmotic efficiency on contaminant transport parameters. *Proceedings XVIth International Conference ISSMGE, Osaka*. Millpress, The Netherlands, pp. 2343–2346.

- Viani, B.V., Low, P.F., and Roth, C.B. (1983) Direct measurement of the relation between interlayer force and interlayer distance in the swelling of montmorillonite. *Journal of Colloid and Interface Science*, **96**, 229–244.
- Winthworth, T.M. and Fritz, S.J. (1994) Electrolyte-induced solute permeability effects in compacted smectite membranes. *Applied Geochemistry*, **9**, 533–546.
- (Received xxxxx 2009; revised xxxxx 2009; Ms. Xxx; A.E. J. Bloggs)